



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 410E-II 1DW410EBKMF708834
Component
Front Differential
Fluid
JOHN DEERE HY-GARD HYD/TRANS (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0205046	JR0145178	JR0133738
Sample Date		Client Info		15 Apr 2024	12 Sep 2022	07 Jun 2022
Machine Age	hrs	Client Info		5439	3972	3515
Oil Age	hrs	Client Info		0	1972	3515
Filter Age	hrs	Client Info		0	500	440
Oil Changed		Client Info		N/A	Changed	Not Changd
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184		18	11	14
Iron	ppm	ASTM D5185m	>500	21	22	19
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	<1	0	<1
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>25	2	<1	<1
Lead	ppm	ASTM D5185m	>25	9	22	14
Copper	ppm	ASTM D5185m	>100	3	5	3
Tin	ppm	ASTM D5185m	>10	6	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	2	3	3
Potassium	ppm	ASTM D5185m	>20	0	2	0
Water		WC Method	>.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		1	2	3
Boron	ppm	ASTM D5185m	6	10	2	2
Barium	ppm	ASTM D5185m	0	4	0	<1
Molybdenum	ppm	ASTM D5185m	0	8	<1	<1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	145	111	88	89
Calcium	ppm	ASTM D5185m	3570	3468	3275	3297
Phosphorus	ppm	ASTM D5185m	1290	987	1007	934
Zinc	ppm	ASTM D5185m	1640	1082	1194	1172
Sulfur	ppm	ASTM D5185m		3938	3629	3261
Visc @ 40°C	cSt	ASTM D445	57.0	55.2	50.6	51.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0205046 **Received** : 16 Apr 2024
Lab Number : 06150666 **Tested** : 17 Apr 2024
Unique Number : 10980744 **Diagnosed** : 18 Apr 2024 - Sean Felton
Test Package : CONST (Additional Tests: PQ)

JRE - GREENSBORO
 411 SOUTH REGIONAL ROAD
 GREENSBORO, NC
 US 27409
 Contact: NICK GALLAHER
 NGALLAHER@JRENET.COM
 T: (336)668-2762
 F: (336)665-9556

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)