WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Area


[W02008185]
Wachine Id
VOLVO A30F 82248


Bogie/Center Axle


{not provided} (11 GAL)

(1101 pro 1100 d) (11 011 12)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. (Customer Sample Comment: W02008185)	Sample Number		Client Info		ML0001602		
	Sample Date		Client Info		12 Apr 2024		
	Machine Age	hrs	Client Info		14578		
	Oil Age	hrs	Client Info		2000		
	Filter Age	hrs	Client Info		2000		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
14/5 A D							
WEAR	Iron	ppm	ASTM D5185m		186		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>15	2		
	Nickel	ppm	ASTM D5185m	>8	1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>10	2		
	Lead	ppm	ASTM D5185m	>4	2		
	Copper	ppm	ASTM D5185m	>50	11		
	Tin	ppm	ASTM D5185m	>4	2		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	12		
	Potassium	ppm		>20	1		
There is no indication of any contamination in the oil.	Water	le le		>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		175		
	Barium	ppm	ASTM D5185m		3		
	Molybdenum	ppm	ASTM D5185m		4		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		29		
	Calcium	ppm	ASTM D5185m		122		
	Phosphorus	ppm	ASTM D5185m		923		
	Zinc	ppm	ASTM D5185m		72		
	Sulfur	ppm	ASTM D5185m		55127		
	Visc @ 40°C	cSt	ASTM D445		255		











Certificate L2367

Report Id: VOLVO0002 [WUSCAR] 06150758 (Generated: 04/18/2024 20:27:09) Rev: 1

Laboratory Sample No.

Lab Number : 06150758 Unique Number : 10980836 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : ML0001602

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received : 16 Apr 2024 **Tested** Diagnosed

: 17 Apr 2024 : 18 Apr 2024 - Don Baldridge

MCCLUNG-LOGAN EQUIPMENT CO - MANASSAS 8450 QUARRY ROAD MANASSAS, VA

US 20110 Contact: MIKE MAYHUGH

MMAYHUGH@MCCLUNG-LOGAN.COM

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (703)393-7344 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (703)393-7844