WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

Area


[W02008186] VOLVO A30D 14025


Bogie/Center Axle


{not provided} (11 GAL)


(1104 provided) (11 data)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. (Customer Sample Comment: W02008186)	Sample Number		Client Info		ML0001594		
	Sample Date		Client Info		12 Apr 2024		
	Machine Age	hrs	Client Info		21012		
	Oil Age	hrs	Client Info		2000		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAD							
WEAR	Iron	ppm	ASTM D5185m		265		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		3		
	Nickel	ppm	ASTM D5185m	>10	2		
	Titanium	ppm	ASTM D5185m		1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>30	2		
	Lead	ppm	ASTM D5185m	>50	<1		
	Copper	ppm	ASTM D5185m	>150	10		
	Tin	ppm	ASTM D5185m	>20	0		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	8		
	Potassium	ppm	ASTM D5185m		3		
There is no indication of any contamination in the oil.	Water	la la	WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		174		
	Barium	ppm	ASTM D5185m		2		
	Molybdenum	ppm	ASTM D5185m		1		
	Manganese	ppm	ASTM D5185m		5		
	Magnesium	ppm	ASTM D5185m		12		
	Calcium	ppm	ASTM D5185m		246		
	Phosphorus	ppm	ASTM D5185m		905		
	Zinc	ppm	ASTM D5185m		122		
	Sulfur	ppm	ASTM D5185m		46088		
	Visc @ 40°C	cSt	ASTM D445		273		

Submitted By: DARRELL ANDES











Certificate L2367

Laboratory Sample No.

Lab Number : 06150762 Unique Number : 10980840

: ML0001594 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 16 Apr 2024 **Tested** : 17 Apr 2024

Diagnosed

: 18 Apr 2024 - Don Baldridge

WILLIAM HAZEL PO BOX 600 CHANTILLY, VA US 20153

Contact: SERVICE MANAGER

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (703)378-8300

F: