



VOLVO A30G 752624

Transmission (Auto)

VOLVO AUTOMATIC TRANSMISSION FLUID AT102 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP417899		
nesample at the next service interval to monitor.	Sample Date		Client Info		25 Mar 2024		
	Machine Age	hrs	Client Info		2021		
	Oil Age	hrs	Client Info		2000		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
				4.00			
WEAR	Iron	ppm	ASTM D5185m		51		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>5	0		
	Titanium Silver	ppm	ASTM D5185m ASTM D5185m	. 5	0		
	Aluminum	ppm	ASTM D5185m		22		
	Lead	ppm ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		18		
	Tin	ppm	ASTM D5185m		4		
	Vanadium	ppm	ASTM D5185m	210	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	13		
There is no indication of any contamination in the fluid.	Potassium	ppm	ASTM D5185m	>20	1		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	LIGHT		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		5		
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185m	187	85		
	Barium	ppm	ASTM D5185m	0.0	<1		
	Molybdenum	ppm	ASTM D5185m	0.0	0		
	Manganese	ppm	ASTM D5185m	0.0	3		
	Magnesium	ppm	ASTM D5185m	6.8	0		
	Calcium	ppm	ASTM D5185m	215	76		
	Phosphorus	ppm	ASTM D5185m	445	203		
	Zinc	ppm	ASTM D5185m	56	4		
	Sulfur	ppm	ASTM D5185m	1336	2096		


Visc @ 40°C


cSt

Contact/Location: JESSE WILSON - VOLVO8531

32.7

ASTM D445 35.3







Contact/Location: JESSE WILSON - VOLVO8531 Page 2 of 2