

## Machine Id

## 24D1001 FGHT-039 Componer New (Unused) Oil

## Air Compressor Oil (--- GAL)

Air Compressor Oil ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
This is a baseline read-out on the submitted sample.	Sample Number		Client Info		HPL006548		
	Sample Date		Client Info		11 Apr 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		0		
	Chromium	ppm	ASTM D5185m		0		
	Nickel		ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		0		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm ppm	ASTM D5185m		0		
	Tin		ASTM D5185m		0		
	Vanadium	ppm ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
		304141	Visual				
CONTAMINATION	Silicon	ppm	ASTM D5185m		<1		
	Potassium	ppm	ASTM D5185m	>20	5		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual		NEG		
FLUID CONDITION	Sodium		ASTM D5185m		1		
	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm					
	Manganese	ppm	ASTM D5185m ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		0		
	Calcium	ppm	ASTM D5185m		0 <1		
	Phosphorus	ppm	ASTM D5185m ASTM D5185m		<1 309		
	Zinc	ppm	ASTM D5185m		0		
	Sulfur	ppm	ASTM D5185m		1852		
	Acid Number (AN)	ppm	ASTM D5185m ASTM D8045		1852		
	Visc @ 40°C	mg KOH/g	ASTM D8045 ASTM D445				
	Visc @ 40°C Visc @ 100°C	cSt			476.3		
		cSt	ASTM D445		37.61		
	Viscosity Index (VI)	Scale	ASTM D2270		120		



