**WEAR** CONTAMINATION **FLUID CONDITION** 


**NORMAL NORMAL NORMAL** 

Machine Id

91083 Component Diesel Engine

MORII DEI VAC 1300 SUPER15W40 (10 GAL)

MOBIL DELVAC 1300 SUPER15W40 (10 GAL)					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		SBP0001951	SBP0002006	SBP0000946
	Sample Date		Client Info		05 Apr 2024	25 Aug 2023	02 Jul 2022
	Machine Age	mls	Client Info		329954	292029	221697
	Oil Age	mls	Client Info		20000	20000	20000
	Filter Age	mls	Client Info		20000	20000	20000
	Oil Changed		Client Info		Changed	Changed	Changed
	Filter Changed		Client Info		Changed	Changed	Changed
	Sample Status				NORMAL	NORMAL	NORMAL
WEAD			AOTM DE 405			40	40
WEAR	Iron	ppm	ASTM D5185m		10	10	10
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1	<1	<1
	Nickel	ppm	ASTM D5185m	>2	0	0	<1
	Titanium	ppm	ASTM D5185m	0	67	0	<1
	Silver	ppm	ASTM D5185m		0	0	<1
	Aluminum	ppm	ASTM D5185m		6	5	6
	Lead	ppm	ASTM D5185m		<1	0	<1
	Copper	ppm	ASTM D5185m		3	4	5
	Tin	ppm	ASTM D5185m	>5	<1	0	1
	Vanadium	ppm	ASTM D5185m		<1	0	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	6	4	4
	Potassium	ppm	ASTM D5185m	>20	21	3	3
There is no indication of any contamination in the oil.	Chlorine	ppm	ASTM D5185m				
	Fuel		WC Method	>5	<1.0	<1.0	<1.0
	Water		WC Method		NEG	NEG	NEG
	Glycol		WC Method		NEG	NEG	NEG
	Soot %	%	*ASTM D7844	>3	0.4	0.5	0.4
	Nitration	Abs/cm	*ASTM D7624	>20	9.5	9.8	9.5
	Sulfation	Abs/.1mm	*ASTM D7415		22.8	23.1	22.4
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	NEG
ELUID CONDITION	Sodium	nnm	ASTM D5185m		4	2	2
FLUID CONDITION	Boron	ppm	ASTM D5185m	0	57	8	
The BN result indicates that there is suitable alkalinity remaining in the	Barium	ppm	ASTM D5185m		0	0	26
oil. The condition of the oil is acceptable for the time in service.		ppm	ASTM D5185m				16
	Molybdenum	ppm	ASTM D5185m	U	18 <1	45 <1	<1
	Manganese Magnesium	ppm	ASTM D5165III	0	436	623	733
	Calcium	ppm	ASTM D5185m	U	1737	1417	1429
		ppm	ASTM D5185m				986
	Phosphorus	ppm			916	778	
	Zinc	ppm	ASTM D5185m		1088	987	1221
	Sulfur Oxidation	ppm Abc/1mm	*ASTM D5185m	> 2F	3755	2799	3990 16.2
	Base Number (BN)	Abs/.1mm			19.2 6.5	22.3 8.3	8.1
	Visc @ 100°C	•	ASTM D2696 ASTM D445			12.7	12.6
	VISC @ 100°C	cSt	49 I IVI D445	14	14.3	12./	12.0





Certificate L2367

Laboratory Sample No.

Test Package : FLEET

: SBP0001951 Lab Number : 06150888 Unique Number: 10980966

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 16 Apr 2024 **Tested** : 17 Apr 2024

Diagnosed

: 18 Apr 2024 - Sean Felton

Sapp Bros. Fleet - Lincoln Location

US Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: