



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
491
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON HP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0905933	WC0792814	WC0792729
Sample Date		Client Info		27 Mar 2024	29 Sep 2023	28 Aug 2023
Machine Age	mls	Client Info		214821	204865	202260
Oil Age	mls	Client Info		5000	0	0
Filter Age	mls	Client Info		5000	0	0
Oil Changed		Client Info		Not Changd	Not Changd	N/A
Filter Changed		Client Info		Not Changd	Not Changd	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	7	16	12
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	<1	2
Lead	ppm	ASTM D5185m	>40	<1	0	<1
Copper	ppm	ASTM D5185m	>330	<1	<1	<1
Tin	ppm	ASTM D5185m	>15	<1	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	2	2	3
Potassium	ppm	ASTM D5185m	>20	14	0	1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.9	0.7
Nitration	Abs/cm	*ASTM D7624	>20	5.6	6.9	6.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.8	19.2	18.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	<1	1
Boron	ppm	ASTM D5185m		2	8	11
Barium	ppm	ASTM D5185m		0	0	<1
Molybdenum	ppm	ASTM D5185m		56	56	59
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		859	879	791
Calcium	ppm	ASTM D5185m		1161	1217	1122
Phosphorus	ppm	ASTM D5185m		1014	1043	944
Zinc	ppm	ASTM D5185m		1213	1276	1137
Sulfur	ppm	ASTM D5185m		3649	3210	3202
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.8	13.3	13.0
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	9.1	8.9	8.9
Visc @ 100°C	cSt	ASTM D445	15.6	13.9	13.6	13.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0905933 **Received** : 16 Apr 2024
Lab Number : 06150943 **Tested** : 17 Apr 2024
Unique Number : 10981021 **Diagnosed** : 17 Apr 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

WAYNE CO SCHOOL BUS GARAGE
 1603 SALEM CHURCH RD
 GOLDSBORO, NC
 US 27530
 Contact: BRANDON BRIGGS
 brandonbriggs@wcps.org
 T:
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)