



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
KENWORTH T880 912 (S/N 1NKZLP0X36J427612)

Component
Diesel Engine

Fluid
SHELL ROTELLA T 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0878961	WC0878919	WC0822273
Sample Date		Client Info		11 Apr 2024	12 Feb 2024	25 Oct 2023
Machine Age	mls	Client Info		178789	170017	155040
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	13	19	21
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	0	<1	<1
Aluminum	ppm	ASTM D5185m	>20	3	5	10
Lead	ppm	ASTM D5185m	>40	<1	<1	<1
Copper	ppm	ASTM D5185m	>330	<1	2	1
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	9	11
Potassium	ppm	ASTM D5185m	>20	18	13	24
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.1	0.7
Nitration	Abs/cm	*ASTM D7624	>20	8.0	8.3	8.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.9	17.8	21.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	0	1
Boron	ppm	ASTM D5185m	316	11	11	14
Barium	ppm	ASTM D5185m	0.0	0	0	0
Molybdenum	ppm	ASTM D5185m	1.2	25	39	54
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	24	255	400	594
Calcium	ppm	ASTM D5185m	2292	2141	1713	1570
Phosphorus	ppm	ASTM D5185m	1064	902	922	989
Zinc	ppm	ASTM D5185m	1160	1154	1131	1279
Sulfur	ppm	ASTM D5185m	4996	3878	3546	2903
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.4	13.2	17.3
Base Number (BN)	mg KOH/g	ASTM D2896	10.1	6.5	▲ 2.9	6.4
Visc @ 100°C	cSt	ASTM D445	15.7	14.6	14.6	14.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0878961 **Received** : 16 Apr 2024
Lab Number : 06151017 **Tested** : 17 Apr 2024
Unique Number : 10981095 **Diagnosed** : 19 Apr 2024 - Sean Felton
Test Package : MOB 1 (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JOHNSON BREEDERS
 3425 HWY 117N
 ROSE HILL, NC
 US 28458

Contact: GREG JONES
 gregory.jones@houseofraeford.com

T: (910)289-6884

F: