



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
MACK R-7
 Component
Diesel Engine
 Fluid
10W30 DURON SEMI (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LP0001220	LP0001335	LP0001107
Sample Date		Client Info		08 Apr 2024	01 Feb 2024	25 Oct 2023
Machine Age	hrs	Client Info		19179	18688	18188
Oil Age	hrs	Client Info		489	450	400
Filter Age	hrs	Client Info		489	450	400
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	8	8	10
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	1	<1	1
Lead	ppm	ASTM D5185m	>40	<1	<1	1
Copper	ppm	ASTM D5185m	>330	<1	<1	1
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	3	3	3
Potassium	ppm	ASTM D5185m	>20	2	0	3
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.2	0.3
Nitration	Abs/cm	*ASTM D7624	>20	8.2	7.6	7.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.1	18.5	19.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		5	4	3
Boron	ppm	ASTM D5185m		5	19	1
Barium	ppm	ASTM D5185m		0	0	4
Molybdenum	ppm	ASTM D5185m		59	60	60
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m		876	902	909
Calcium	ppm	ASTM D5185m		1207	992	1019
Phosphorus	ppm	ASTM D5185m		1128	1034	1007
Zinc	ppm	ASTM D5185m		1275	1228	1223
Sulfur	ppm	ASTM D5185m		3212	3028	3137
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.6	14.8	15.6
Base Number (BN)	mg KOH/g	ASTM D2896		8.17	8.07	11.06
Visc @ 100°C	cSt	ASTM D445		11.0	11.0	11.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LP0001220
Lab Number : 06151299
Unique Number : 10981377
Test Package : MOB 2

Received : 16 Apr 2024
Tested : 18 Apr 2024
Diagnosed : 18 Apr 2024 - Wes Davis

SELECT DEMO
 40 LOWELL RD
 SALEM, NH
 US 03079

Contact: STAN DOGIL
 SDOGIL@SELECTDEMOSERVICES.COM
 T: (603)401-0147
 F: (603)458-7389

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)