WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL


Machine Id


31262


Component Right Final Drive

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		WC0924567	WC0856752	WC085678
	Sample Date		Client Info		13 Apr 2024	11 Oct 2023	11 Oct 202
	Machine Age	hrs	Client Info		827	349	349
	Oil Age	hrs	Client Info		250	349	349
	Filter Age	hrs	Client Info		250	349	349
	Oil Changed		Client Info		Changed	Changed	Changed
	Filter Changed		Client Info		Changed	Changed	Changed
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR	Iron	ppm	ASTM D5185m	>500	12	133	140
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1	3	3
	Nickel	ppm	ASTM D5185m		0	1	1
	Titanium	ppm	ASTM D5185m		0	<1	<1
	Silver	ppm	ASTM D5185m		0	0	0
	Aluminum	ppm	ASTM D5185m	>25	1	<1	2
	Lead	ppm	ASTM D5185m	>25	0	<1	<1
	Copper	ppm	ASTM D5185m	>50	<1	<1	<1
	Tin	ppm	ASTM D5185m	>10	0	0	0
	Vanadium	ppm	ASTM D5185m		0	0	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	5	10	9
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2	3	4
	Water		WC Method	>0.2	NEG	NEG	NEG
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORM
	Odor	scalar	*Visual	NORML	NORML	NORML	NORM
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	<1	5	5
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	143	4	8
	Barium	ppm	ASTM D5185m	200	0	12	28
	Molybdenum	ppm	ASTM D5185m	12	13	<1	<1
	Manganese	ppm	ASTM D5185m		0	2	2
	Magnesium	ppm	ASTM D5185m	12	53	1	1
	Calcium	ppm	ASTM D5185m	150	178	12	20
	Phosphorus	ppm	ASTM D5185m	1650	2328	1261	1328
	Zinc	ppm	ASTM D5185m		143	31	30
	Sulfur	ppm	ASTM D5185m		18066	27413	28712
	Visc @ 40°C	cSt	ASTM D445	143 act/Loca	112	196	196











Certificate L2367

Laboratory Sample No.

: WC0924567 Lab Number : 06151377 Unique Number : 10981455 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 16 Apr 2024 **Tested** : 18 Apr 2024

Diagnosed : 18 Apr 2024 - Wes Davis **SULLIVAN EASTERN INC** 2860 C SLATER RD

MORRISVILLE, NC US 27560

Contact: SCOTT SULLIVAN ssullivan@sullivaneastern.com T: (919)484-8993

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (919)484-2136 Contact/Location: SCOTT SULLIVAN - MSCDUR