



WEAR	<b>ABNORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**142204**  
Component  
**Diesel Engine**  
Fluid  
**{not provided} (--- QTS)**

### RECOMMENDATION

No corrective action is recommended at this time. Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>IL06151599</b>	IL05952089	---
Sample Date		Client Info		<b>29 Feb 2024</b>	31 Aug 2023	---
Machine Age	hrs	Client Info		<b>4038</b>	3195	---
Oil Age	hrs	Client Info		<b>0</b>	0	---
Filter Age	hrs	Client Info		<b>0</b>	0	---
Oil Changed		Client Info		<b>N/A</b>	N/A	---
Filter Changed		Client Info		<b>N/A</b>	N/A	---
Sample Status				<b>ABNORMAL</b>	ABNORMAL	---

### WEAR

The aluminum level is abnormal. All other component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	<b>35</b>	29	---
Chromium	ppm	ASTM D5185m	>20	<b>3</b>	2	---
Nickel	ppm	ASTM D5185m	>4	<b>0</b>	0	---
Titanium	ppm	ASTM D5185m		<b>0</b>	<1	---
Silver	ppm	ASTM D5185m	>3	<b>0</b>	0	---
Aluminum	ppm	ASTM D5185m	>20	<b>▲ 27</b>	<b>▲ 24</b>	---
Lead	ppm	ASTM D5185m	>40	<b>0</b>	0	---
Copper	ppm	ASTM D5185m	>330	<b>2</b>	2	---
Tin	ppm	ASTM D5185m	>15	<b>0</b>	<1	---
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	0	---
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	---

### CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	<b>5</b>	5	---
Potassium	ppm	ASTM D5185m	>20	<b>21</b>	38	---
Fuel	%	ASTM D3524	>5	<b>&lt;1.0</b>	<1.0	---
Water		WC Method	>0.2	<b>NEG</b>	NEG	---
Glycol		WC Method		<b>NEG</b>	NEG	---
Soot %	%	*ASTM D7844	>3	<b>0.8</b>	0.6	---
Nitration	Abs/cm	*ASTM D7624	>20	<b>9.4</b>	9.0	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>19.4</b>	20.1	---
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	---
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	---
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	---

### FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>2</b>	3	---
Boron	ppm	ASTM D5185m		<b>2</b>	0	---
Barium	ppm	ASTM D5185m		<b>0</b>	0	---
Molybdenum	ppm	ASTM D5185m		<b>57</b>	61	---
Manganese	ppm	ASTM D5185m		<b>&lt;1</b>	<1	---
Magnesium	ppm	ASTM D5185m		<b>840</b>	1013	---
Calcium	ppm	ASTM D5185m		<b>1005</b>	1182	---
Phosphorus	ppm	ASTM D5185m		<b>909</b>	1048	---
Zinc	ppm	ASTM D5185m		<b>1101</b>	1262	---
Sulfur	ppm	ASTM D5185m		<b>3150</b>	3594	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>15.6</b>	16.6	---
Base Number (BN)	mg KOH/g	ASTM D2896		<b>9.2</b>	9.3	---
Visc @ 100°C	cSt	ASTM D445		<b>11.9</b>	12.9	---


▲ Aluminum (ppm)




Ferrous Alloys




FT-IR (Direct Trend)




Non-ferrous Metals




Base Number




Viscosity @ 100°C



Viscosity @ 100°C



Base Number



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : IL06151599  
**Lab Number** : 06151599  
**Unique Number** : 10981677  
**Test Package** : FLEET ( Additional Tests: FuelDilution, PercentFuel )

**RUSH TRUCK LEASING - CINCINNATI IDEALEASE**  
 11777 HIGHWAY DRIVE  
 CINCINNATI, OH  
 US 45241  
 Contact: ROBERT BAIER  
 baierr@rushenterprises.com  
 T: (513)657-7901  
 F: (513)733-0537

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)