
**WEAR** CONTAMINATION **FLUID CONDITION**  **NORMAL NORMAL NORMAL** 

Machine Id

## **TAKEUCHI TL12V2 CS-157**

Diesel Engine

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0195249		
	Sample Date		Client Info		16 Apr 2024		
	Machine Age	hrs	Client Info		2431		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
VEAR	Iron	ppm	ASTM D5185m	>100	16		
	Chromium	ppm	ASTM D5185m		<1		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	- 1	0		
	Silver	ppm	ASTM D5185m	>3	0		
	Aluminum	ppm	ASTM D5185m		3		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		2		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m	7.0	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
ONTAMINATION	Ciliana		ACTM DE10E	05			
ONTAMINATION	Silicon	ppm	ASTM D5185m		6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		3		
	Fuel		WC Method		<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol	0/	WC Method	0	NEG		
	Soot %	% Ala a /ave	*ASTM D7844		0.6		
	Nitration	Abs/cm	*ASTM D7624	>20	8.6		
	Sulfation	Abs/.1mm	*ASTM D7415		18.5		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
	Boron	ppm	ASTM D5185m		2		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		4		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		66		
	Calcium	ppm	ASTM D5185m		2448		
	Phosphorus	ppm	ASTM D5185m		935		
	Zinc	ppm	ASTM D5185m		1099		
	Sulfur	ppm	ASTM D5185m		3401		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	11.6		
	Base Number (BN)	mg KOH/g	ASTM D2896		7.1		
	Visc @ 100°C	cSt	ASTM D445		13.9		







Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Lab Number : 06151792 Unique Number : 10981870

: JR0195249 Received **Tested** Diagnosed

: 18 Apr 2024

: 18 Apr 2024 - Wes Davis

: 17 Apr 2024

13236 NATIONAL PIKE CLEAR SPRING, MD

**CREEKSTONE LANDSCAPING** 

US 21722 Contact: HALEY

Test Package : CONST (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: