



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
HAL PANNELL (S/N RG-6081A303564)
Component
Starboard Genset
Fluid
CHEVRON DELO 710 LE (7 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0062356	MW0066510	MW0066523
Sample Date		Client Info		16 Mar 2024	14 Feb 2024	05 Jan 2024
Machine Age	hrs	Client Info		0	1500	960
Oil Age	hrs	Client Info		530	514	476
Filter Age	hrs	Client Info		530	514	476
Oil Changed		Client Info		Changed	Changed	N/A
Filter Changed		Client Info		N/A	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	24	23	33
Chromium	ppm	ASTM D5185m	>4	1	1	2
Nickel	ppm	ASTM D5185m	>2	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m	>12	3	2	1
Lead	ppm	ASTM D5185m	>17	<1	0	1
Copper	ppm	ASTM D5185m	>70	<1	<1	2
Tin	ppm	ASTM D5185m	>15	0	0	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	6	7	9
Potassium	ppm	ASTM D5185m	>20	2	0	2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.3	0.2	0.3
Nitration	Abs/cm	*ASTM D7624	>20	9.1	9.0	9.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.1	16.2	16.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<1	2	0
Boron	ppm	ASTM D5185m		34	41	43
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		48	47	52
Manganese	ppm	ASTM D5185m		0	<1	1
Magnesium	ppm	ASTM D5185m		13	37	12
Calcium	ppm	ASTM D5185m		3524	3325	3671
Phosphorus	ppm	ASTM D5185m		4	14	15
Zinc	ppm	ASTM D5185m	10	4	18	0
Sulfur	ppm	ASTM D5185m		2163	2119	2352
Oxidation	Abs/.1mm	*ASTM D7414	>25	10.2	10.3	10.9
Base Number (BN)	mg KOH/g	ASTM D2896	9.2	6.1	6.3	6.2
Visc @ 100°C	cSt	ASTM D445	15.5	14.1	14.1	14.2


FT-IR (Direct Trend)




Ferrous Alloys




Base Number




Non-ferrous Metals




Viscosity @ 100°C



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0062356
Lab Number : 06151813
Unique Number : 10981891
Test Package : MAR 2

Received : 17 Apr 2024
Tested : 18 Apr 2024
Diagnosed : 18 Apr 2024 - Wes Davis

AMERICAN COMMERCIAL LINES
 PO BOX 610, 1701 E. MARKET STREET
 JEFFERSONVILLE, IN
 US 47130
 Contact: RONALD SCHNEIDER
 ronald.schneider@bargeacbl.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: (812)288-1644