



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
[PMOAS3340190]
 Machine Id
KOHLER 500R07071 325709
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DC0035248	DC0027712	DC0004747
Sample Date		Client Info		02 Apr 2024	04 Apr 2023	07 Apr 2020
Machine Age	yrs	Client Info		1	0	1669
Oil Age	yrs	Client Info		1	12	50
Filter Age	yrs	Client Info		1	0	50
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>200	4	7	6
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	<1
Titanium	ppm	ASTM D5185m	>2	0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>30	1	1	<1
Lead	ppm	ASTM D5185m	>30	2	0	2
Copper	ppm	ASTM D5185m	>30	1	2	2
Tin	ppm	ASTM D5185m	>15	2	4	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>30	12	12	22
Potassium	ppm	ASTM D5185m	>20	2	<1	<1
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.1	0.2
Nitration	Abs/cm	*ASTM D7624	>20	3.6	3.7	5
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.1	15.1	13.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	<1	2	3
Boron	ppm	ASTM D5185m	250	429	351	2
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	47	36	<1
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	450	38	113	1239
Calcium	ppm	ASTM D5185m	3000	3808	3114	390
Phosphorus	ppm	ASTM D5185m	1150	1153	919	1028
Zinc	ppm	ASTM D5185m	1350	1224	1053	1153
Sulfur	ppm	ASTM D5185m	4250	4415	6170	9539
Oxidation	Abs/.1mm	*ASTM D7414	>25	7.9	7.3	5.6
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	8.9	8.2	---
Visc @ 100°C	cSt	ASTM D445	14.4	14.2	13.9	15.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : DC0035248 **Received** : 17 Apr 2024
Lab Number : 06151838 **Tested** : 18 Apr 2024
Unique Number : 10981916 **Diagnosed** : 18 Apr 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

KELLY GENERATOR & EQUIPMENT INC
 1955 DALE LN
 OWINGS, MD
 US 20736
 Contact: LESLIE SNURR
 LSNURR@KGE.COM
 T: (410)257-5225
 F: (410)257-5227

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)