



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[16W16011]
 Machine Id
JOHN DEERE 210G 1FF210GXCNF530112
 Component
Hydraulic System
 Fluid
JOHN DEERE HYDRAU (36 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. (Customer Sample Comment: 16W16011)

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0206879	JR0185691	JR0173265
Sample Date		Client Info		15 Apr 2024	30 Oct 2023	02 Jun 2023
Machine Age	hrs	Client Info		1471	959	518
Oil Age	hrs	Client Info		1471	959	0
Filter Age	hrs	Client Info		512	959	0
Oil Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Filter Changed		Client Info		Not Chngd	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	12	14	18
Iron	ppm	ASTM D5185m	>32	2	4	2
Chromium	ppm	ASTM D5185m	>9	0	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>9	0	<1	<1
Lead	ppm	ASTM D5185m	>28	0	0	0
Copper	ppm	ASTM D5185m	>50	<1	1	1
Tin	ppm	ASTM D5185m	>5	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>11	<1	<1	0
Potassium	ppm	ASTM D5185m	>20	11	<1	<1
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	19818	3447	2082
Particles >6µm		ASTM D7647	>20000	1730	258	351
Particles >14µm		ASTM D7647	>640	17	19	13
Particles >21µm		ASTM D7647	>160	6	6	2
Particles >38µm		ASTM D7647	>40	0	1	0
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	21/18/11	19/15/11	18/16/11
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	2	1	<1
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		<1	20	3
Molybdenum	ppm	ASTM D5185m		0	<1	0
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		0	0	4
Calcium	ppm	ASTM D5185m	87	1	0	6
Phosphorus	ppm	ASTM D5185m	727	427	529	528
Zinc	ppm	ASTM D5185m	900	18	47	50
Sulfur	ppm	ASTM D5185m	1500	108	46	145
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.18	0.18	0.16
Visc @ 40°C	cSt	ASTM D445	65	46.7	47.2	47.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0206879 **Received** : 17 Apr 2024
Lab Number : 06151876 **Tested** : 18 Apr 2024
Unique Number : 10981954 **Diagnosed** : 19 Apr 2024 - Don Baldrige
Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - CASTLE HAYNE
 113 CROWATAN ROAD
 CASTLE HAYNE, NC
 US 28429-5819

Contact: WILMINGTON SHOP

todd.simmons@jamesriverequipment.com; canastasio@wearcheck.com; canastasio@we

T: (910)675-9211

F: