WEAR CONTAMINATION FLUID CONDITION

NORMAL

ABNORMAL

NORMAL

Machine Id

NO INFO ON SIF/BOTTLE

Hydraulic System

AW HYDRAULIC OIL ISO 46 (--- GAL)

PECOMMENDATION	T+		Mathaal	1 : na 14 / A la na	2	LUnkamid	L lintam (O
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
We recommend you service the filters on this component. Resample at the next service interval to monitor. Please specify the component make and model with your next sample.	Sample Number Sample Date		Client Info		JR0209264 16 Apr 2024		
	Machine Age	hrs	Client Info		0 Apr 2024		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed	1113	Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status		Onone into		ABNORMAL		
WEAR	PQ		ASTM D8184		19		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		4		
	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		2		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m	NONE	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	<1		
	Potassium	ppm	ASTM D5185m	>20	11		
There is a high amount of particulates present in the oil.	Water		WC Method	>0.1	NEG		
	Particles >4µm		ASTM D7647	>5000	<u> </u> 51212		
	Particles >6µm		ASTM D7647	>1300	13639		
	Particles >14μm		ASTM D7647	>160	689		
	Particles >21µm		ASTM D7647	>40	<u> </u>		
	Particles >38µm		ASTM D7647	>10	^ 22		
	Particles >71μm		ASTM D7647		3		
	Oil Cleanliness		ISO 4406 (c)	>19/17/14	<u>^</u> 23/21/17		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	LIGHT		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3		
	Boron	ppm	ASTM D5185m	5	0		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	5	0		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m	25	40		
	Calcium	ppm	ASTM D5185m	200	25		
	Phosphorus	ppm	ASTM D5185m		244		
	Zinc	ppm	ASTM D5185m	370	276		
	Sulfur	ppm	ASTM D5185m	2500	780		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.42		
	Visc @ 40°C	cSt	ASTM D445	46	43.5		





Certificate L2367

Laboratory Sample No. Lab Number

: JR0209264 : 06151897 Unique Number : 10981975

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 17 Apr 2024 **Tested**

: 18 Apr 2024 : 19 Apr 2024 - Don Baldridge Diagnosed Test Package : CONST (Additional Tests: PQ)

JRE - GARNER 4161 AUBURN CHURCH RD GARNER, NC US 27529

Contact: RALEIGH SHOP sean.betts@jamesriverequipment.com;catherine.anastasio@wearcheck.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (919)779-5432 Contact/Location: RALEIGH SHOP - RWMGAR

T: (919)614-2260