



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
21062
 Component
Compressor
 Fluid
INGERSOLL-RAND TURBOBLEND 46 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		CCSI2011215	CCSI2012915	CCSI2011170
Sample Date		Client Info		15 Apr 2024	15 Nov 2022	24 Mar 2022
Machine Age	hrs	Client Info		28900	13095	9245
Oil Age	hrs	Client Info		4000	0	9245
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	0	0	0
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m		0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>25	0	0	0
Lead	ppm	ASTM D5185m	>25	0	0	0
Copper	ppm	ASTM D5185m	>50	0	0	0
Tin	ppm	ASTM D5185m	>15	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	0	<1	<1
Potassium	ppm	ASTM D5185m	>20	10	<1	0
Water	%	ASTM D6304	>0.1	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>10000	26176	311	2761
Particles >6µm		ASTM D7647	>2500	6965	63	172
Particles >14µm		ASTM D7647	>320	273	4	17
Particles >21µm		ASTM D7647	>80	54	1	6
Particles >38µm		ASTM D7647	>20	4	1	0
Particles >71µm		ASTM D7647	>4	0	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	22/20/15	15/13/9	19/15/11
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	0	<1
Boron	ppm	ASTM D5185m		0	0	2
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		0	0	0
Calcium	ppm	ASTM D5185m		0	0	0
Phosphorus	ppm	ASTM D5185m		15	11	13
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m		3	67	68
Acid Number (AN)	mg KOH/g	ASTM D8045		0.13	0.12	0.13
Visc @ 40°C	cSt	ASTM D445	46	44.3	44.8	44.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : CCSI2011215 **Received** : 17 Apr 2024
Lab Number : 06151953 **Tested** : 19 Apr 2024
Unique Number : 10982031 **Diagnosed** : 19 Apr 2024 - Don Baldrige
Test Package : IND 2 (Additional Tests: KF, PrtCount)

WESTINGHOUSE ELECTRIC CO.
 5801 BLUFF RD
 COLUMBIA, SC
 US 29250
 Contact: CHUCK LLOYD
 chuck.lloydj@irco.com
 T: (803)647-3609
 F: (803)695-4161

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)