

WEAR CONTAMINATION FLUID CONDITION


ABNORMAL NORMAL NORMAL



JOHN DEERE 524K 1DW524KZLFF672597

Front Axle

	Tost	11014	Mathani	Lips II / A I	C	I Baken d	11:
RECOMMENDATION	Test Sample Number	UOM	Method Client Info	Limit/Abn	Current JR0212937	History1	History2
No corrective action is recommended at this time. The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.	Sample Number		Client Info		12 Apr 2024		
	Machine Age	hrs	Client Info		6530		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed	1110	Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				ABNORMAL		
MEAD	PQ		ACTM DO104		00		
WEAR	Iron	nnm	ASTM D5185m	∼750	36 239		
Bearing and/or bushing wear is indicated. All other component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1 <1		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m	>10	<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>21	<1		
	Lead	ppm	ASTM D5185m	>49	<u> </u>		
	Copper	ppm	ASTM D5185m	>101	228		
	Tin	ppm	ASTM D5185m	>10	2 3		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>31	14		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		11		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	11		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	100		
	Barium	ppm	ASTM D5185m	0	<1		
	Molybdenum	ppm	ASTM D5185m	0	1		
	Manganese	ppm	ASTM D5185m		5		
	Magnesium	ppm	ASTM D5185m	145	33		
	Calcium	ppm	ASTM D5185m	3570	3217		
	Phosphorus	ppm	ASTM D5185m	1290	1140		
	Zinc	ppm	ASTM D5185m	1640	1268		
	Sulfur	ppm	ASTM D5185m		6431		
	Visc @ 40°C	cSt	ASTM D445	57.0	49.0		





Report Id: RWMGAR [WUSCAR] 06152234 (Generated: 04/22/2024 11:34:22) Rev: 1

Laboratory Sample No.

Lab Number : 06152234 **Unique Number** : 10982312

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0212937

Received **Tested** Diagnosed

: 17 Apr 2024 : 18 Apr 2024

: 22 Apr 2024 - Don Baldridge

JRE - GARNER 4161 AUBURN CHURCH RD GARNER, NC

US 27529 Contact: RALEIGH SHOP

F: (919)779-5432

Test Package : CONST (Additional Tests: PQ) Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

sean.betts@jamesriverequipment.com;catherine.anastasio@wearcheck.com T: (919)614-2260