WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

Machine Id

WIRTGEN W120FTI 27100213

Component

Rear Right Final Drive

{not provided} (--- GAL)

{not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		JR0210288		
	Sample Date		Client Info		17 Apr 2024		
	Machine Age	hrs	Client Info		57		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		33		
	Iron	ppm	ASTM D5185m	>500	34		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		1		
	Titanium	ppm	ASTM D5185m		1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	9		
	Lead	ppm	ASTM D5185m	>25	<1		
	Copper	ppm	ASTM D5185m	>50	<1		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Cilioan		ACTM DE10Em	. 75	20		
CONTAMINATION	Silicon	ppm	ASTM D5185m		39		
There is no indication of any contamination in the oil.	Potassium Water	ppm	ASTM D5185m		3 NEC		
	Silt	cooler	WC Method *Visual	>0.2 NONE	NEG NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		6		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		1		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		1		
	Magnesium	ppm	ASTM D5185m		9		
	Calcium	ppm	ASTM D5185m		118		
	Phosphorus	ppm	ASTM D5185m		400		
	Zinc	ppm	ASTM D5185m		26		
	Sulfur	ppm	ASTM D5185m		392		
Report Id: JAMWIN [WUSCAR] 06153393 (Generated: 04/22/2024 17:48:09) Rev: 1	Visc @ 40°C	cSt	ASTM D445 Cont	act/Loca	232 ation: PHIL D	/ AUGHERT\	 Y - JAMWIN





Certificate L2367

Laboratory Sample No.

Lab Number : 06153393 Unique Number : 10983471

Test Package : CONST (Additional Tests: PQ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0210288 Received : 18 Apr 2024 **Tested** : 19 Apr 2024

: 22 Apr 2024 - Sean Felton Diagnosed

245 YARDMASTER COURT STEPHENSON, VA US 22656-1761 Contact: PHIL DAUGHERTY

> pdaugherty@jamesriverequipment.com T: x:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (540)693-2588

Contact/Location: PHIL DAUGHERTY - JAMWIN

JRE - STEPHENSON