WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

[701221 HERC]

VOLVO ECR223 315400

Rear Right Final Drive

| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|---|--------------------|--------|----------------------------|------------|-------------|----------|----------|
| Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample. | Sample Number | | Client Info | | VCP443715 | | |
| | Sample Date | | Client Info | | 15 Apr 2024 | | |
| | Machine Age | hrs | Client Info | | 852 | | |
| | Oil Age | hrs | Client Info | | 0 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Not Changd | | |
| | Filter Changed | | Client Info | | Not Changd | | |
| | Sample Status | | | | NORMAL | | |
| VEAR | lvon | | ACTM DE10Em | . F00 | 100 | | |
| WEAR All component wear rates are normal. | Iron | ppm | ASTM D5185m | | 133 | | |
| | Chromium Nickel | ppm | ASTM D5185m ASTM D5185m | | 4 | | |
| | Titanium | ppm | ASTM D5185m | >10 | <1 <1 | | |
| | Silver | ppm | ASTM D5185m | | 0 | | |
| | Aluminum | ppm | ASTM D5185m | \25 | 2 | | |
| | Lead | ppm | ASTM D5185m | | 1 | | |
| | Copper | ppm | ASTM D5185m | | - <1 | | |
| | Tin | ppm | ASTM D5185m | | <1 | | |
| | Vanadium | ppm | ASTM D5185m | 7.0 | <1 | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| | | | | | | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >75 | 25 | | |
| There is no indication of any contamination in the oil. | Potassium | ppm | ASTM D5185m | >20 | 3 | | |
| | Water | | | >0.2 | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | LIGHT | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.2 | NEG | | |
| LUID CONDITION | Sodium | ppm | ASTM D5185m | | <1 | | |
| The condition of the oil is acceptable for the time in service. | Boron | ppm | ASTM D5185m | | 0 | | |
| | Barium | ppm | ASTM D5185m | | 3 | | |
| | Molybdenum | ppm | ASTM D5185m | | 2 | | |
| | Manganese | ppm | ASTM D5185m | | 4 | | |
| | Magnesium | ppm | ASTM D5185m | | 1 | | |
| | Calcium | ppm | ASTM D5185m | | 12 | | |
| | Phosphorus | ppm | ASTM D5185m | | 311 | | |
| | Zinc | ppm | ASTM D5185m | | 9 | | |
| | Sulfur | ppm | ASTM D5185m | | 16507 | | |







Certificate L2367

Laboratory Sample No.

: VCP443715 Lab Number : 06153495 Unique Number: 10983573 Test Package : MOB 1

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 18 Apr 2024 **Tested** : 19 Apr 2024

Diagnosed : 22 Apr 2024 - Sean Felton

ALTA EQUIPMENT/FLAGLER CONSTRUCTION EQUIPMENT LLC 8418 PALM RIVER ROAD

TAMPA, FL US 33619 Contact: KENNY HANEY khaney@flaglerce.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

T: (813)630-0077 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (813)630-2233