WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL

Machine Id

FREIGHTLINER 11131

Component Diesel Engine

MOBIL 15W40 (20 QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		WC0912563	WC0891627	WC082656
Resample at the next service interval to monitor.	Sample Date		Client Info		27 Mar 2024	04 Jan 2024	13 Jun 202
	Machine Age	mls	Client Info		201662	185428	192556
	Oil Age	mls	Client Info		0	0	0
	Filter Age	mls	Client Info		0	0	0
	Oil Changed		Client Info		Changed	Changed	Changed
	Filter Changed		Client Info		Changed	Changed	Changed
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR	Iron	ppm	ASTM D5185m	>130	19	4	20
	Chromium	ppm	ASTM D5185m	>10	0	<1	<1
All component wear rates are normal.	Nickel	ppm	ASTM D5185m	>4	0	0	<1
	Titanium	ppm	ASTM D5185m	>2	0	0	0
	Silver	ppm	ASTM D5185m	>2	0	0	0
	Aluminum	ppm	ASTM D5185m	>20	5	2	9
	Lead	ppm	ASTM D5185m	>20	<1	0	0
	Copper	ppm	ASTM D5185m	>125	1	<1	<1
	Tin	ppm	ASTM D5185m	>4	<1	0	<1
	Vanadium	ppm	ASTM D5185m		0	0	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	3	4	4
	Potassium	ppm	ASTM D5185m	>20	8	2	2
There is no indication of any contamination in the oil.	Fuel	1-1-	WC Method		<1.0	<1.0	<1.0
	Water		WC Method		NEG	NEG	NEG
	Glycol		WC Method		NEG	NEG	NEG
	Soot %	%	*ASTM D7844	>6	0.8	0.1	0.2
	Nitration	Abs/cm	*ASTM D7624		6.8	4.6	5.0
	Sulfation	Abs/.1mm	*ASTM D7415	>30	19.8	17.8	18.2
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORM
	Odor	scalar	*Visual	NORML	NORML	NORML	NORM
	Emulsified Water		*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>118	7	0	<1
	Boron	ppm	ASTM D5185m		2	1	<1
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0	0	0
	Molybdenum	ppm	ASTM D5185m		61	60	60
	Manganese	ppm	ASTM D5185m		<1	0	<1
	Magnesium	ppm	ASTM D5185m		964	997	1013
	Calcium	ppm	ASTM D5185m		1049	1075	1039
	Phosphorus	ppm	ASTM D5185m		1073	1066	1062
	Zinc	ppm	ASTM D5185m		1244	1210	1313
	Sulfur	ppm	ASTM D5185m		3749	3666	4103
	Oxidation	Abs/.1mm	*ASTM D7414	>25	14.6	13.4	13.7
	Base Number (BN)		ASTM D2896	720	10.0	10.2	11.1
	Dasc Halliber (DIV)	my Romy	ASTM D2030		. 5.0	13.7	13.8







Certificate L2367

Laboratory Sample No.

Lab Number : 06153616 Unique Number: 10983694

: WC0912563 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 18 Apr 2024 **Tested** : 19 Apr 2024

Diagnosed : 19 Apr 2024 - Wes Davis

198 PARK PLAZA DRIVE WINSTON SALEM, NC US 27105

SALEM NATIONALEASE CORPORATION

Contact: Audrey Hopkins

Audrey.Hopkins@salemcorp.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

T: (336)767-9642 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: x: