



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
CHARLIE M EVERHART
Machine Id
[CHARLIE M EVERHART] 007 534782-7
Component
Port Genset
Fluid
CHEVRON DELO 400 LE 15W40 (5 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0064475	MW0064471	MW0055292
Sample Date		Client Info		01 Apr 2024	01 Mar 2024	01 Feb 2024
Machine Age	hrs	Client Info		8124	3178	7440
Oil Age	hrs	Client Info		400	165	129
Filter Age	hrs	Client Info		400	165	129
Oil Changed		Client Info		N/A	Changed	Not Changd
Filter Changed		Client Info		N/A	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	18	11	10
Chromium	ppm	ASTM D5185m	>4	0	<1	0
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m	>12	5	5	4
Lead	ppm	ASTM D5185m	>17	3	1	1
Copper	ppm	ASTM D5185m	>70	10	6	11
Tin	ppm	ASTM D5185m	>15	2	<1	2
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	17	13	6
Potassium	ppm	ASTM D5185m	>20	3	1	0
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.2	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	9.5	5.9	7.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.5	22.9	23.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	4	1
Boron	ppm	ASTM D5185m		409	404	365
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		131	131	128
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		694	675	686
Calcium	ppm	ASTM D5185m		1618	1554	1579
Phosphorus	ppm	ASTM D5185m	1200	769	775	743
Zinc	ppm	ASTM D5185m	1300	898	884	896
Sulfur	ppm	ASTM D5185m	3200	2944	2798	2584
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.8	16.7	18.1
Base Number (BN)	mg KOH/g	ASTM D2896	9.6	9.4	9.5	9.1
Visc @ 100°C	cSt	ASTM D445	15.7	13.3	13.6	13.3


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : MW0064475

Lab Number : 06153700

Unique Number : 10983778

Test Package : MAR 2

Received : 18 Apr 2024

Tested : 19 Apr 2024

Diagnosed : 19 Apr 2024 - Wes Davis

INGRAM BARGE

900 S 3RD ST

PADUCAH, KY

US 42003

Contact: JAMES ADAIR

james.adair@ingrambarga.com

T: (270)415-4467

F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)