

Machine Id **NOT GIVEN WC0903213** Component **Diesel Engine** DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		WC0903213		
	Sample Date		Client Info		03 Apr 2024		
	Machine Age	mls	Client Info		104019		
brand, type, and viscosity of the on on your next sample.	Oil Age	mls	Client Info		60000		
	Filter Age	mls	Client Info		60000		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		4		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		0		
'	Nickel	ppm	ASTM D5185m	>4	0		
	Titanium	ppm	ASTM D5185m	0	6		
	Silver	ppm	ASTM D5185m		0		
	Aluminum Lead	ppm	ASTM D5185m ASTM D5185m		2 <1		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m		י <1		
	Vanadium	ppm ppm	ASTM D5185m	>15	< 1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
		Scalai	visual				
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	3		
	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.7		
	Nitration	Abs/cm	*ASTM D7624	>20	6.7		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	20.0		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>158	3		
	Boron	ppm	ASTM D5185m		270		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		58		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m	450	589		
	Calcium	ppm	ASTM D5185m		1377		
	Phosphorus	ppm	ASTM D5185m	1150	934		
	Zinc	ppm	ASTM D5185m	1350	1036		
	Sulfur	ppm	ASTM D5185m	4250	3727		
	O distantia a	AL / 4	****	05	10.0		

Oxidation

Visc @ 100°C cSt

13.3


8.4

13.6

Abs/.1mm *ASTM D7414 >25

ASTM D445 14.4

Base Number (BN) mg KOH/g ASTM D2896 8.5



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 SALEM NATIONALEASE CORPORATION Sample No. Received 198 PARK PLAZA DRIVE : WC0903213 : 18 Apr 2024 Lab Number : 06153724 Tested : 20 Apr 2024 WINSTON SALEM, NC Diagnosed Unique Number : 10983802 : 20 Apr 2024 - Wes Davis US 27105 Test Package : FLEET **Contact: Audrey Hopkins** Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. Audrey.Hopkins@salemcorp.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (336)767-9642 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: x:

\$8

Contact/Location: Audrey Hopkins - SALWIN Page 2 of 2