WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL



729084
Component
Diesel Engine
Fluid

PETRO CANADA 15W40 (--- GAL)

	¬ -)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		GFL0111251		
	Sample Date		Client Info		09 Apr 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		600		
	Filter Age	hrs	Client Info		600		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>120	27		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	>2	0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m	>40	<1		
	Copper	ppm	ASTM D5185m	>330	2		
	Tin	ppm	ASTM D5185m	>15	1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		0		
	Fuel		WC Method		<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol	0/	WC Method	4	NEG		
	Soot %	%	*ASTM D7844		0.6		
	Nitration	Abs/cm	*ASTM D7624	>20	12.7		
	Sulfation	Abs/.1mm	*ASTM D7415		21.4		
	Silt Debris	scalar	*Visual	NONE	NONE NONE		
	Sand/Dirt	scalar	*Visual	NONE NONE	NONE		
		scalar			NORML		
	Appearance Odor	scalar scalar	*Visual *Visual	NORML NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
<u></u>		Scalai	Visuai	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		6		
	Boron	ppm	ASTM D5185m		0		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		57		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		915		
	Calcium	ppm	ASTM D5185m		1116		
	Phosphorus	ppm	ASTM D5185m		914		
	Zinc	ppm	ASTM D5185m		1148		
	Sulfur	ppm	ASTM D5185m		3424		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	18.7		
	Base Number (BN)	mg KOH/g	ASTM D2896		6.6		
	Visc @ 100°C	cSt	ASTM D445		13.0		







Certificate L2367

Report Id: GFL960B [WUSCAR] 06154085 (Generated: 04/23/2024 10:57:47) Rev: 1

Laboratory Sample No.

: GFL0111251 Lab Number : 06154085 Unique Number: 10989508 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 19 Apr 2024

Tested : 22 Apr 2024 Diagnosed : 22 Apr 2024 - Wes Davis

GFL Environmental - 960B - Pittsfield HC

1335 W. Washington Pittsfield, IL US 62363

Contact: David Bradshaw david.bradshaw@gflenv.com T:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: