


Store 1 - Cowen [RO#149061] JOHN DEERE 648L2 1DW648LBKNF715642


Transmission (Manual)


JOHN DEERE HY-GARD HYD/TRANS (15 GAL)

| | ····· | | | | | | |
|---|--------------------|--------|----------------------------|-------------|-------------|-------------|----------|
| RECOMMENDATION | Test | UOM | Method | Limit/Abn | | History1 | History2 |
| Resample at the next service interval to monitor. | Sample Number | | Client Info | | LEC0048936 | LEC0041081 | |
| | Sample Date | | Client Info | | 17 Apr 2024 | 17 Jul 2023 | |
| | Machine Age | hrs | Client Info | | 834 | 427 | |
| | Oil Age | hrs | Client Info | | 834 | 427 | |
| | Filter Age | hrs | Client Info | | 834 | 427 | |
| | Oil Changed | | Client Info | | Not Changd | Not Changd | |
| | Filter Changed | | Client Info | | Not Changd | Not Changd | |
| | Sample Status | | | | NORMAL | NORMAL | |
| WEAR | PQ | | ASTM D8184 | <u>\</u> 95 | 18 | 17 | |
| | Iron | ppm | ASTM D0104 ASTM D5185m | | 12 | 9 | |
| All component wear rates are normal. | Chromium | | ASTM D5185m | | 0 | <1 | |
| | Nickel | ppm | ASTM D5185m | | 0 | 0 | |
| | | ppm | | >0 | | | |
| | Titanium Silver | ppm | ASTM D5185m ASTM D5185m | . 7 | 0 | <1 | |
| | | ppm | | | 0 | 0 | |
| | Aluminum | ppm | ASTM D5185m | | <1 | 0 | |
| | Lead | ppm | ASTM D5185m | | <1 | <1 | |
| | Copper | ppm | ASTM D5185m | | 4 | 2 | |
| | Tin | ppm | ASTM D5185m | >10 | <1 | <1 | |
| | Vanadium | ppm | ASTM D5185m | | <1 | <1 | |
| | White Metal | scalar | *Visual | NONE | NONE | NONE | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | NONE | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >125 | 5 | 4 | |
| There is no indication of any contamination in the fluid. | Potassium | ppm | ASTM D5185m | >20 | 0 | <1 | |
| | Water | | WC Method | | NEG | NEG | |
| | Silt | scalar | *Visual | NONE | NONE | NONE | |
| | Debris | scalar | *Visual | NONE | NONE | NONE | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | |
| | Appearance | scalar | *Visual | NORML | NORML | NORML | |
| | Odor | scalar | *Visual | NORML | NORML | NORML | |
| | Emulsified Water | | *Visual | >0.1 | NEG | NEG | |
| | | | | | | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | | 10 | 10 | |
| The condition of the fluid is acceptable for the time in service. | Boron | ppm | ASTM D5185m | | 0 | 0 | |
| | Barium | ppm | ASTM D5185m | | 0 | 0 | |
| | Molybdenum | ppm | ASTM D5185m | 0 | 0 | 0 | |
| | Manganese | ppm | ASTM D5185m | | <1 | <1 | |
| | Magnesium | ppm | ASTM D5185m | | 86 | 94 | |
| | Calcium | ppm | ASTM D5185m | 3570 | 3262 | 3519 | |
| | Phosphorus | ppm | ASTM D5185m | 1290 | 970 | 1023 | |
| | Zinc | ppm | ASTM D5185m | 1640 | 1062 | 1252 | |
| | Sulfur | ppm | ASTM D5185m | | 3744 | 4160 | |
| | Visc @ 40°C | cSt | ASTM D445 | 57.0 | 47.5 | 48.2 | |
| | | | | | | | |

Submitted By: STORE 2 - BEAVER - CASEY TONEY







Submitted By: STORE 2 - BEAVER - CASEY TONEY Page 2 of 2

Apr17/24