



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[W51042]
 Machine Id
JOHN DEERE 750K 1T0750KXAJF328757
 Component
Left Inner Final Drive
 Fluid
JOHN DEERE HY-GARD HYD/TRANS (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0211495	JR0180406	JR0125098
Sample Date		Client Info		16 Apr 2024	11 Oct 2023	25 Mar 2022
Machine Age	hrs	Client Info		5990	5352	2965
Oil Age	hrs	Client Info		638	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>1250	21	36	33
Iron	ppm	ASTM D5185m	>750	31	59	46
Chromium	ppm	ASTM D5185m	>9	0	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>40	<1	1	1
Lead	ppm	ASTM D5185m	>15	<1	0	1
Copper	ppm	ASTM D5185m	>40	<1	0	<1
Tin	ppm	ASTM D5185m	>10	<1	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	7	6	4
Potassium	ppm	ASTM D5185m	>20	0	<1	0
Water		WC Method	>0.075	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	1	<1	1
Boron	ppm	ASTM D5185m	6	2	<1	7
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	2	0	<1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	145	100	97	101
Calcium	ppm	ASTM D5185m	3570	3236	3479	3558
Phosphorus	ppm	ASTM D5185m	1290	951	994	1033
Zinc	ppm	ASTM D5185m	1640	1026	1300	1207
Sulfur	ppm	ASTM D5185m		4074	3636	3331
Visc @ 40°C	cSt	ASTM D445	57.0	52.3	51.0	52.0



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0211495 **Received** : 19 Apr 2024
Lab Number : 06154698 **Tested** : 22 Apr 2024
Unique Number : 10990121 **Diagnosed** : 22 Apr 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

JRE - ASHLAND
 11047 LEADBETTER RD
 ASHLAND, VA
 US 23005
 Contact: DAVID ZIEG
 dzieg@jamesriverequipment.com
 T: (804)798-6001
 F: (804)798-0292

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)