

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL

Machine Id HAMM H12iP H2352105 Component Drum Gearbox Fluid

{not provided} (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

WEAR

All component wear rates are normal.

CONTAMINATION


There is no indication of any contamination in the oil.


FLUID CONDITION


The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0209096		
Sample Date		Client Info		17 Apr 2024		
Machine Age	hrs	Client Info		1986		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Filter Changed		Client Info		None		
Sample Status				NORMAL		
				•••		
PQ		ASTM D8184	000	26		
Iron	ppm	ASTM D5185m	>200	13		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m		0		
Lead	ppm	ASTM D5185m		0		
Copper	ppm	ASTM D5185m		6		
Tin	ppm	ASTM D5185m		<1		
Vanadium	ppm	ASTM D5185m		<1		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m		5		
Potassium	ppm	ASTM D5185m	>20	0		
Water		WC Method	>0.2	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Sodium	ppm	ASTM D5185m		1		
Boron	ppm	ASTM D5185m		174		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		4		
Phosphorus	ppm	ASTM D5185m		1237		
Zinc	ppm	ASTM D5185m		3		
Sulfur	ppm	ASTM D5185m		29427		
Visc @ 40°C	cSt	ASTM D445		114		

Submitted By: JOHN GUASCHINO







Submitted By: JOHN GUASCHINO Page 2 of 2