

## Machine Id **JOHN DEERE 370E 1DW370ETAHF680855** Componer Front Differential

## JOHN DEERE HY-GARD HYD/TRANS (--- QTS)


JUNN DEERE NT-GARD NTD/ TRANS ( QI	13)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		WE0006948	WE0004363	
	Sample Date		Client Info		16 Apr 2024	05 Jul 2023	
	Machine Age	hrs	Client Info		6000	4986	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Not Changd	
	Filter Changed		Client Info		Changed	Changed	
	Sample Status				NORMAL	NORMAL	
WEAR	PQ		ASTM D8184			10	
WEAN	Iron	000	ASTM D6184 ASTM D5185m	. 500	22 33	19 21	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m			0	
	Nickel	ppm	ASTM D5185m		0	0	
	Titanium	ppm	ASTM D5185m	>10	0	0	
	Silver	ppm ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>25	0	<1	
	Lead	ppm	ASTM D5185m		17	16	
	Copper	ppm	ASTM D5185m		12	7	
	Tin	ppm	ASTM D5185m		<1	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	~ 75	3	2	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		0	0	
	Water	ppm	WC Method	>.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		5	3	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	0	0	
	Barium	ppm	ASTM D5185m	0	2	0	
	Molybdenum	ppm	ASTM D5185m	0	<1	<1	
	Manganese	ppm	ASTM D5185m		2	<1	
	Magnesium	ppm	ASTM D5185m	145	96	95	
	Calcium	ppm	ASTM D5185m	3570	3547	3326	
	Phosphorus	ppm	ASTM D5185m	1290	1063	963	
	Zinc	ppm	ASTM D5185m	1640	1251	1161	
	Sulfur	ppm	ASTM D5185m		4218	3802	
	N# 0.4615	<u> </u>				10 -	

Visc @ 40°C

cSt

ASTM D445 57.0 50.4 Contact/Location: SCOTT GOOD - WARNOR

48.5



Sample No. : WE0006948 Received P.O. BOX 412 : 22 Apr 2024 Lab Number : 06156221 Tested : 23 Apr 2024 NORTHPORT, AL Unique Number : 10991644 Diagnosed : 23 Apr 2024 - Wes Davis US 35476 Test Package : CONST (Additional Tests: PQ) Contact: SCOTT GOOD Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. sgood@warriortractor.com \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (205)339-0300 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: