



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
(YA141291)

Machine Id
10865

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (50 GAL)

RECOMMENDATION

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0117999	GFL0088491	GFL0088482
Sample Date		Client Info		21 Apr 2024	05 Dec 2023	08 Aug 2023
Machine Age	hrs	Client Info		0	12342	8800
Oil Age	hrs	Client Info		0	0	11598
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	Changed	Changed
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	ABNORMAL	SEVERE

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	2	16	33
Chromium	ppm	ASTM D5185m	>5	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>15	2	3	3
Lead	ppm	ASTM D5185m	>25	0	0	<1
Copper	ppm	ASTM D5185m	>100	0	<1	1
Tin	ppm	ASTM D5185m	>4	<1	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










Fuel content negligible. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	4	10	6
Potassium	ppm	ASTM D5185m	>20	<1	2	2
Fuel	%	ASTM D3524	>3.0	0.3	▲ 6.0	▲ 10.7
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	0.1	0.2	0.4
Nitration	Abs/cm	*ASTM D7624	>20	5.3	11.9	11.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.4	21.9	22.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		7	▲ 369	44
Boron	ppm	ASTM D5185m	0	11	22	4
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	59	70	55
Manganese	ppm	ASTM D5185m	0	<1	0	<1
Magnesium	ppm	ASTM D5185m	1010	909	872	759
Calcium	ppm	ASTM D5185m	1070	1055	1022	1015
Phosphorus	ppm	ASTM D5185m	1150	1051	922	895
Zinc	ppm	ASTM D5185m	1270	1192	1174	1085
Sulfur	ppm	ASTM D5185m	2060	3549	2689	2480
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.9	22.0	23.4
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.8	7.4	6.0
Visc @ 100°C	cSt	ASTM D445	15.4	13.8	13.3	▲ 12.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0117999 **Received** : 22 Apr 2024
Lab Number : 06156787 **Tested** : 25 Apr 2024
Unique Number : 10992210 **Diagnosed** : 25 Apr 2024 - Wes Davis
Test Package : FLEET (Additional Tests: PercentFuel)

GFL Environmental - 112 - New Bern
 705 Airport Road
 New Bern, NC
 US 28560
 Contact: Marquis Williams
 marquis.williams@gflenv.com
 T:
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)