



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
BOBSP 7351
 Component
Gearbox
 Fluid
MOBIL MOBILGEAR 600 XP ISO 150 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PTK0001399	PTK0000289	PTK0000347
Sample Date		Client Info		19 Apr 2024	09 Nov 2023	13 Jun 2023
Machine Age	wks	Client Info		0	0	0
Oil Age	wks	Client Info		0	0	0
Filter Age	wks	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>200	2	0	3
Chromium	ppm	ASTM D5185m	>10	<1	0	0
Nickel	ppm	ASTM D5185m	>10	<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		<1	0	0
Aluminum	ppm	ASTM D5185m	>25	3	0	0
Lead	ppm	ASTM D5185m	>50	<1	0	<1
Copper	ppm	ASTM D5185m	>200	1	<1	1
Tin	ppm	ASTM D5185m	>10	<1	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	LIGHT	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION













The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>50	1	<1	3
Potassium	ppm	ASTM D5185m	>20	2	0	1
Water		WC Method	>0.2	NEG	NEG	NEG
Particles >4µm		ASTM D7647		933	1243	604
Particles >6µm		ASTM D7647	>2500	206	321	156
Particles >14µm		ASTM D7647	>320	19	21	17
Particles >21µm		ASTM D7647	>80	6	5	5
Particles >38µm		ASTM D7647	>20	0	1	0
Particles >71µm		ASTM D7647	>4	0	0	0
Oil Cleanliness		ISO 4406 (c)	>18/15	15/11	16/12	14/11
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		0	<1	0
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	2
Molybdenum	ppm	ASTM D5185m		<1	0	0
Manganese	ppm	ASTM D5185m		<1	0	0
Magnesium	ppm	ASTM D5185m		1	0	<1
Calcium	ppm	ASTM D5185m		0	2	2
Phosphorus	ppm	ASTM D5185m		331	295	302
Zinc	ppm	ASTM D5185m		6	11	8
Sulfur	ppm	ASTM D5185m		16200	14752	14990
Acid Number (AN)	mg KOH/g	ASTM D8045		0.77	0.68	0.73
Visc @ 40°C	cSt	ASTM D445	150	152	154	149



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PTK0001399 **Received** : 22 Apr 2024
Lab Number : 06156895 **Tested** : 23 Apr 2024
Unique Number : 10992318 **Diagnosed** : 23 Apr 2024 - Wes Davis
Test Package : MOB 2 (Additional Tests: PrtCount)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

GRAPHIC PACKAGING

1500 NICHOLAS BLVD
ELK GROVE, IL
US 60017

Contact: TONY HILDY
anthonyhildy@graphicpkg.com
T: (847)437-1700

F: