



VOLVO

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	MARGINAL



Area
[SWA538927]
 Machine Id
VOLVO A40G 352783
 Component
Diesel Engine
 Fluid
VOLVO ULTRA DIESEL ENGINE OIL 15W40 VDS-3 (--- GAL)

RECOMMENDATION

The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP438874	VCP436039	VCP413404
Sample Date		Client Info		19 Apr 2024	04 Nov 2023	26 Aug 2023
Machine Age	hrs	Client Info		4611	3520	2904
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				MARGINAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	4	5	5
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>25	3	2	2
Lead	ppm	ASTM D5185m	>40	0	<1	0
Copper	ppm	ASTM D5185m	>330	<1	2	3
Tin	ppm	ASTM D5185m	>15	1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION













Fuel content negligible. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	3	3	3
Potassium	ppm	ASTM D5185m	>20	0	0	<1
Fuel	%	ASTM D3524	>6.0	2.4	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>20	7.9	7.3	6.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.8	18.7	18.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil.

Sodium	ppm	ASTM D5185m		1	<1	2
Boron	ppm	ASTM D5185m	2.5	2	0	<1
Barium	ppm	ASTM D5185m	0.0	0	0	0
Molybdenum	ppm	ASTM D5185m	0.7	63	58	61
Manganese	ppm	ASTM D5185m	0.0	<1	0	<1
Magnesium	ppm	ASTM D5185m	256	979	1015	1041
Calcium	ppm	ASTM D5185m	2057	1116	1058	1150
Phosphorus	ppm	ASTM D5185m	935	1060	1050	1100
Zinc	ppm	ASTM D5185m	1223	1254	1322	1379
Sulfur	ppm	ASTM D5185m	4079	3485	3161	3999
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.3	14.3	13.8
Base Number (BN)	mg KOH/g	ASTM D2896	10	8.3	8.6	9.1
Visc @ 100°C	cSt	ASTM D445	15.0	▲ 12.3	12.9	13.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : VCP438874 **Received** : 23 Apr 2024
Lab Number : 06157349 **Tested** : 25 Apr 2024
Unique Number : 10992772 **Diagnosed** : 25 Apr 2024 - Jonathan Hester
Test Package : MOB 1 (Additional Tests: FuelDilution, PercentFuel, TBN)

PALM BEACH AGGREGATES INC
 PO BOX 700, 20125 STATE RD 80
 LOXAHATCHEE, FL
 US 33470
 Contact: WILLIAM GONZALEZ
 wgonzalez@palmbeachag.com
 T: (561)723-0194
 F: (561)798-5380

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)