WEAR CONTAMINATION **FLUID CONDITION**


NORMAL ABNORMAL NORMAL

Machine Id

LOW FIRMNESS

Hydraulic System

AW HYDRAULIC OIL ISO 46 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Little or no information is provided as to the component and lubricant being tested. Recommendations are therefore generic in nature and may not apply to the current application. Please forward information as to equipment type, reservoir capacity, lubricant type and any pertinent information to allow for a more accurate assessment. We advise that you perform a filter service, and use off-line filtration to improve the cleanliness of the system fluid. We recommend an early resample to monitor this condition. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		WC0859523	WC0859521	WC0859519
	Sample Date		Client Info		12 Apr 2024	13 Mar 2024	12 Feb 2024
	Machine Age	wks	Client Info		0	0	0
	Oil Age	wks	Client Info		0	0	0
	Filter Age	wks	Client Info		0	0	0
	Oil Changed		Client Info		N/A	N/A	N/A
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status				ABNORMAL	ABNORMAL	ATTENTION
WEAR	Iron	ppm	ASTM D5185m	>20	<1	0	0
	Chromium	ppm	ASTM D5185m	>20	<1	0	0
All component wear rates are normal.	Nickel	ppm	ASTM D5185m	>20	<1	0	0
	Titanium	ppm	ASTM D5185m		<1	0	0
	Silver	ppm	ASTM D5185m		0	0	0
	Aluminum	ppm	ASTM D5185m	>20	2	0	0
	Lead	ppm	ASTM D5185m		0	0	0
	Copper	ppm	ASTM D5185m		<1	0	0
	Tin	ppm	ASTM D5185m		<1	0	0
	Vanadium	ppm	ASTM D5185m		<1	0	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m		<1	0	1
There is a moderate amount of particulates (2 to 100 microns in size) present in the oil. The system cleanliness is above the acceptable limit for the target ISO 4406 cleanliness code.	Potassium	ppm	ASTM D5185m	>20	<1	0	0
	Water		WC Method	>0.05	NEG	NEG	NEG
	Particles >4µm		ASTM D7647	>2500	<u> </u>	<u> </u>	1366
	Particles >6µm		ASTM D7647	>640	4 3140	△ 4093	695
	Particles >14μm		ASTM D7647	>80	402	<u>440</u>	114
	Particles >21μm		ASTM D7647	>20	<u> </u>	<u> </u>	37
	Particles >38μm		ASTM D7647	>4	5	5	3
	Particles >71μm		ASTM D7647	>3	0	0	0
	Oil Cleanliness		ISO 4406 (c)	>18/16/13	<u> </u>	<u>^</u> 21/19/16	18/17/14
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0	<1	0
	Boron	ppm	ASTM D5185m	5	0	0	0
The AN level is acceptable for this fluid. The oil is still serviceable provided that the contaminant(s) can be reduced to acceptable levels.	Barium	ppm	ASTM D5185m		0	0	0
	Molybdenum	ppm	ASTM D5185m		<1	0	0
	Manganese	ppm	ASTM D5185m		0	0	0
	Magnesium	ppm	ASTM D5185m	25	<1	0	0
	Calcium	ppm	ASTM D5185m		42	40	44
	Phosphorus	ppm	ASTM D5185m		314	320	328
	Zinc	ppm	ASTM D5185m		437	412	398
	Sulfur	ppm	ASTM D5185m		870	911	828
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.36	0.38	0.447
	Visc @ 40°C	cSt	ASTM D445		43.4	49.4	43.2







Certificate L2367

Laboratory Sample No. Lab Number

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 06157653 Unique Number: 10993076

: WC0859523 Test Package : IND 2

Received : 23 Apr 2024 **Tested** Diagnosed

: 24 Apr 2024 : 24 Apr 2024 - Wes Davis **WOODBRIDGE CORPORATION**

2399 SOUTH STONE MOUNTAIN LITHONIA, GA US 30058

Contact: MIKE FRYER

mike_fryer@woodbridgegroup.com T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: