

## Machine Id

## JOHN DEERE 220DW 1FF220DWHDD041203

## Front Differential

## TDH FLUID SAE 75W80 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0212392		
	Sample Date		Client Info		22 Apr 2024		
	Machine Age	hrs	Client Info		8874		
	Oil Age	hrs	Client Info		8874		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		41		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		53		
	Chromium	ppm	ASTM D5185m		1		
	Nickel	ppm	ASTM D5185m	>10	5		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		7		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	10		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	3		
	Water		WC Method	>.2	NEG		
	Silt	scalar	*Visual	NONE	LIGHT		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		16		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	10	114		
	Barium	ppm	ASTM D5185m	10	1		
	Molybdenum	ppm	ASTM D5185m	10	<1		
	Manganese	ppm	ASTM D5185m		6		
	Magnesium	ppm	ASTM D5185m	100	10		
	Calcium	ppm	ASTM D5185m	3500	3408		
	Phosphorus	ppm	ASTM D5185m	1150	1082		
	Zinc	ppm	ASTM D5185m	1150	1371		
	Sulfur	ppm	ASTM D5185m	5000	3579		
		-					


Visc @ 40°C


cSt

ASTM D445 48

Submitted By: RENN MASHBURN

54.7





Submitted By: RENN MASHBURN Page 2 of 2

Apr22/24