

## JOHN DEERE 524 P 1DW524PAPPLS17696 Component Rear Axle

{not provided} (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0204656		
	Sample Date		Client Info		22 Apr 2024		
	Machine Age	hrs	Client Info		2216		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		107		
WEAN				750	107		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		260		
	Chromium	ppm	ASTM D5185m		2		
	Nickel	ppm	ASTM D5185m	>10	3		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	01	0		
	Aluminum	ppm	ASTM D5185m		3		
	Lead	ppm	ASTM D5185m ASTM D5185m		7		
	Copper	ppm			29		
	Tin	ppm	ASTM D5185m	>10	2		
	Vanadium	ppm	ASTM D5185m		<1 NONE		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>31	19		
There is no indication of any contamination in the sample.	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	5		
	Boron	ppm	ASTM D5185m		1		
The condition of the sample is acceptable for the time in service.	Barium	ppm	ASTM D5185m		4		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		8		
	Magnesium	ppm	ASTM D5185m		81		
	Calcium	ppm	ASTM D5185m		2661		
	Phosphorus	ppm	ASTM D5185m		870		
	Zinc	ppm	ASTM D5185m		998		
		66.01					
	Sulfur	ppm	ASTM D5185m		3066		


Visc @ 40°C


ASTM D445

cSt

Contact/Location: JUSTIN WILLIAMS - JAMGRE

55.1





Contact/Location: JUSTIN WILLIAMS - JAMGRE Page 2 of 2

Apr22/24