

WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**





Machine Id **VOLVO A40G 341237 Transmission (Auto)**

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number	OOM	Client Info	Little / toll	ASC0010496	VCP421559	VCP411920
	Sample Date		Client Info		18 Apr 2024	31 Oct 2023	27 Jul 2023
	Machine Age	hrs	Client Info		8907	7991	7468
	Oil Age	hrs	Client Info		1000	0	0
	Filter Age	hrs	Client Info		1000	0	0
	Oil Changed		Client Info		Not Changd	N/A	Changed
	Filter Changed		Client Info		Changed	Changed	Changed
	Sample Status				NORMAL	NORMAL	ABNORMAL
WEAR	Iron	ppm	ASTM D5185m	>160	45	29	24
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>5	0	0	0
	Nickel	ppm	ASTM D5185m	>5	2	2	2
	Titanium	ppm	ASTM D5185m		0	0	0
	Silver	ppm	ASTM D5185m	>5	0	0	0
	Aluminum	ppm	ASTM D5185m	>50	16	17	14
	Lead	ppm	ASTM D5185m	>50	0	0	0
	Copper	ppm	ASTM D5185m	>225	18	17	13
	Tin	ppm	ASTM D5185m	>10	1	2	1
	Vanadium	ppm	ASTM D5185m		0	0	<1
	White Metal	scalar	*Visual	NONE	NONE	NONE	▲ MODEF
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	17	9	7
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	1	3	3
	Water		WC Method	>0.1	NEG	NEG	NEG
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	▲ MODER
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3	6	4
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	187	83	85	110
	Barium	ppm	ASTM D5185m	0.0	<1	0	0
	Molybdenum	ppm	ASTM D5185m		0	0	0
	Manganese	ppm	ASTM D5185m		3	0	<1
	Magnesium	ppm	ASTM D5185m		<1	0	0
	Calcium	ppm	ASTM D5185m		86	66	67
	Phosphorus	ppm	ASTM D5185m		209	174	191
	Zinc	ppm	ASTM D5185m		3	4	0
	Sulfur	ppm	ASTM D5185m		2273	1817	2288
	Visc @ 40°C	cSt	ASTM D445	35.3	27.7	27.7	28.2











Certificate L2367

Laboratory Sample No.

: ASC0010496 Lab Number : 06158162

Unique Number : 10993585 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 23 Apr 2024

Tested : 24 Apr 2024 Diagnosed : 25 Apr 2024 - Jonathan Hester HANSON SOUTHEAST

NC HWY 117 ERWIN, NC US 28339

Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: