



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
TEREX AC80-2 7955 (S/N 48268)
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DC0021577	DC0031998	DC0021654
Sample Date		Client Info		02 Apr 2024	11 Dec 2023	21 Dec 2022
Machine Age	hrs	Client Info		2049	1287	1631
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	N/A	Changed
Sample Status				NORMAL	MARGINAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	6	11	10
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	2	2
Lead	ppm	ASTM D5185m	>40	0	<1	<1
Copper	ppm	ASTM D5185m	>330	3	5	4
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION













There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	3	5	3
Potassium	ppm	ASTM D5185m	>20	2	5	6
Fuel	%	ASTM D3524	>5	<1.0	▲ 4.2	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.7	0.5
Nitration	Abs/cm	*ASTM D7624	>20	6.3	7.4	7.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.2	17.8	18.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	<1	2	2
Boron	ppm	ASTM D5185m	250	3	10	105
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	2	4	29
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	450	52	58	83
Calcium	ppm	ASTM D5185m	3000	2329	2234	2050
Phosphorus	ppm	ASTM D5185m	1150	886	820	898
Zinc	ppm	ASTM D5185m	1350	1047	990	1062
Sulfur	ppm	ASTM D5185m	4250	4220	4059	3349
Oxidation	Abs/.1mm	*ASTM D7414	>25	9.0	10.5	13.1
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	7.3	6.8	7.6
Visc @ 100°C	cSt	ASTM D445	14.4	12.3	11.9	12.7



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : DC0021577 **Received** : 23 Apr 2024
Lab Number : 06158313 **Tested** : 25 Apr 2024
Unique Number : 10993736 **Diagnosed** : 25 Apr 2024 - Jonathan Hester
Test Package : MOB 1 (Additional Tests: FuelDilution, PercentFuel, TBN)

ABERDEEN PROVING GROUND
 6721 RARITON AVENUE
 ABERDEEN, MD
 US 21005
 Contact: TONY DAVIS
 tdavis@vacranetworks.com
 T: (410)688-1725
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)