



**James River  
Equipment**

**OIL ANALYSIS REPORT**

|                 |               |
|-----------------|---------------|
| WEAR            | <b>NORMAL</b> |
| CONTAMINATION   | <b>NORMAL</b> |
| FLUID CONDITION | <b>NORMAL</b> |



Machine Id  
**JOHN DEERE 700K 1T0700KXCGF292315**  
Component  
**Left Final Drive**  
Fluid  
**JOHN DEERE HY-GARD HYD/TRANS (--- GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

| Test           | UOM | Method      | Limit/Abn | Current            | History1    | History2    |
|----------------|-----|-------------|-----------|--------------------|-------------|-------------|
| Sample Number  |     | Client Info |           | <b>JR0207855</b>   | JR0185028   | JR0160569   |
| Sample Date    |     | Client Info |           | <b>15 Apr 2024</b> | 10 Oct 2023 | 30 Mar 2023 |
| Machine Age    | hrs | Client Info |           | <b>10880</b>       | 10306       | 9691        |
| Oil Age        | hrs | Client Info |           | <b>574</b>         | 1162        | 547         |
| Filter Age     | hrs | Client Info |           | <b>0</b>           | 0           | 0           |
| Oil Changed    |     | Client Info |           | <b>Not Changd</b>  | Changed     | Not Changd  |
| Filter Changed |     | Client Info |           | <b>N/A</b>         | N/A         | N/A         |
| Sample Status  |     |             |           | <b>NORMAL</b>      | NORMAL      | NORMAL      |

**WEAR**

All component wear rates are normal.

|              |        |             |       |              |      |      |
|--------------|--------|-------------|-------|--------------|------|------|
| PQ           |        | ASTM D8184  | >1250 | <b>55</b>    | 132  | 155  |
| Iron         | ppm    | ASTM D5185m | >750  | <b>70</b>    | 243  | 123  |
| Chromium     | ppm    | ASTM D5185m | >9    | <b>1</b>     | 2    | 2    |
| Nickel       | ppm    | ASTM D5185m | >10   | <b>&lt;1</b> | <1   | 0    |
| Titanium     | ppm    | ASTM D5185m |       | <b>&lt;1</b> | <1   | 0    |
| Silver       | ppm    | ASTM D5185m |       | <b>0</b>     | 0    | 0    |
| Aluminum     | ppm    | ASTM D5185m | >40   | <b>6</b>     | 11   | <1   |
| Lead         | ppm    | ASTM D5185m | >15   | <b>&lt;1</b> | 0    | 0    |
| Copper       | ppm    | ASTM D5185m | >40   | <b>&lt;1</b> | 0    | <1   |
| Tin          | ppm    | ASTM D5185m | >10   | <b>&lt;1</b> | 0    | 0    |
| Vanadium     | ppm    | ASTM D5185m |       | <b>&lt;1</b> | <1   | <1   |
| White Metal  | scalar | *Visual     | NONE  | <b>NONE</b>  | NONE | NONE |
| Yellow Metal | scalar | *Visual     | NONE  | <b>NONE</b>  | NONE | NONE |

**CONTAMINATION**






There is no indication of any contamination in the oil.

|                  |        |             |        |              |       |       |
|------------------|--------|-------------|--------|--------------|-------|-------|
| Silicon          | ppm    | ASTM D5185m | >75    | <b>19</b>    | 44    | 21    |
| Potassium        | ppm    | ASTM D5185m | >20    | <b>2</b>     | 2     | 3     |
| Water            |        | WC Method   | >0.075 | <b>NEG</b>   | NEG   | NEG   |
| Silt             | scalar | *Visual     | NONE   | <b>NONE</b>  | NONE  | NONE  |
| Debris           | scalar | *Visual     | NONE   | <b>NONE</b>  | NONE  | NONE  |
| Sand/Dirt        | scalar | *Visual     | NONE   | <b>NONE</b>  | NONE  | NONE  |
| Appearance       | scalar | *Visual     | NORML  | <b>NORML</b> | NORML | NORML |
| Odor             | scalar | *Visual     | NORML  | <b>NORML</b> | NORML | NORML |
| Emulsified Water | scalar | *Visual     | >0.075 | <b>NEG</b>   | NEG   | NEG   |

**FLUID CONDITION**

The condition of the oil is acceptable for the time in service.

|             |     |             |      |              |      |      |
|-------------|-----|-------------|------|--------------|------|------|
| Sodium      | ppm | ASTM D5185m | >51  | <b>0</b>     | <1   | 2    |
| Boron       | ppm | ASTM D5185m | 6    | <b>0</b>     | 1    | 23   |
| Barium      | ppm | ASTM D5185m | 0    | <b>0</b>     | 0    | 3    |
| Molybdenum  | ppm | ASTM D5185m | 0    | <b>1</b>     | 0    | 0    |
| Manganese   | ppm | ASTM D5185m |      | <b>&lt;1</b> | 2    | 3    |
| Magnesium   | ppm | ASTM D5185m | 145  | <b>101</b>   | 98   | 2    |
| Calcium     | ppm | ASTM D5185m | 3570 | <b>3390</b>  | 3404 | 23   |
| Phosphorus  | ppm | ASTM D5185m | 1290 | <b>1016</b>  | 965  | 267  |
| Zinc        | ppm | ASTM D5185m | 1640 | <b>1215</b>  | 1243 | 20   |
| Sulfur      | ppm | ASTM D5185m |      | <b>3601</b>  | 3459 | 9636 |
| Visc @ 40°C | cSt | ASTM D445   | 57.0 | <b>54.9</b>  | 52.6 | 53.7 |



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : JR0207855 **Received** : 23 Apr 2024  
**Lab Number** : 06158529 **Tested** : 25 Apr 2024  
**Unique Number** : 10993952 **Diagnosed** : 25 Apr 2024 - Wes Davis  
**Test Package** : CONST ( Additional Tests: PQ )

**TENNOCA CONSTRUCTION**  
 PO BOX 2379  
 CANDLER, NC  
 US 28715  
 Contact: MARK ROSS  
 mark@tennoca.com  
 T: (828)665-8331  
 F:

Certificate L2367  
 To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)