



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
428035-402343
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0118161	GFL0109146	GFL0109238
Sample Date		Client Info		10 Apr 2024	15 Mar 2024	16 Feb 2024
Machine Age	hrs	Client Info		12115	11972	4052
Oil Age	hrs	Client Info		700	300	600
Filter Age	hrs	Client Info		700	0	0
Oil Changed		Client Info		Not Changd	N/A	Changed
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>110	16	17	48
Chromium	ppm	ASTM D5185m	>4	<1	0	2
Nickel	ppm	ASTM D5185m	>2	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	<1	3
Lead	ppm	ASTM D5185m	>45	5	10	▲ 47
Copper	ppm	ASTM D5185m	>85	3	2	7
Tin	ppm	ASTM D5185m	>4	<1	0	3
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>30	5	5	9
Potassium	ppm	ASTM D5185m	>20	0	0	1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.5	0.4	0.8
Nitration	Abs/cm	*ASTM D7624	>20	10.2	8.5	13.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.6	20.4	26.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	4	7
Boron	ppm	ASTM D5185m	0	<1	<1	0
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	65	63	70
Manganese	ppm	ASTM D5185m	0	<1	0	<1
Magnesium	ppm	ASTM D5185m	1010	1030	1104	1171
Calcium	ppm	ASTM D5185m	1070	1152	1226	1292
Phosphorus	ppm	ASTM D5185m	1150	1089	1189	1238
Zinc	ppm	ASTM D5185m	1270	1352	1471	1527
Sulfur	ppm	ASTM D5185m	2060	3331	3923	3124
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.8	17.3	26.9
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.4	8.8	6.3
Visc @ 100°C	cSt	ASTM D445	15.4	14.7	14.6	15.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0118161
Lab Number : 06158910
Unique Number : 10994333
Test Package : FLEET

Received : 24 Apr 2024
Tested : 25 Apr 2024
Diagnosed : 25 Apr 2024 - Wes Davis

GFL Environmental - 822 - Springfield Hauling
 2120 West Bennett Street
 Springfield, MO
 US 65807

Contact: Dennis Moore
 dennis.moore@gflenv.com

T: (417)403-3641

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: