



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
EPIROC D65-10 G22SED0578
 Component
Compressor
 Fluid
ATLAS COPCO PAROIL S (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0212402	JR0202416	JR0202627
Sample Date		Client Info		19 Apr 2024	07 Mar 2024	02 Feb 2024
Machine Age	hrs	Client Info		3243	3023	2744
Oil Age	hrs	Client Info		220	0	0
Filter Age	hrs	Client Info		220	0	0
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Filter Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184		14	10	4
Iron	ppm	ASTM D5185m	>50	0	6	<1
Chromium	ppm	ASTM D5185m	>5	<1	<1	<1
Nickel	ppm	ASTM D5185m		<1	<1	<1
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>15	2	2	1
Lead	ppm	ASTM D5185m	>65	<1	<1	<1
Copper	ppm	ASTM D5185m	>65	<1	<1	<1
Tin	ppm	ASTM D5185m	>10	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>35	<1	2	<1
Potassium	ppm	ASTM D5185m	>20	<1	1	1
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		<1	1	0
Boron	ppm	ASTM D5185m	0	0	0	0
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	<1	<1	<1
Manganese	ppm	ASTM D5185m	0	0	0	<1
Magnesium	ppm	ASTM D5185m	0	<1	<1	<1
Calcium	ppm	ASTM D5185m	0	5	5	28
Phosphorus	ppm	ASTM D5185m	100	27	74	45
Zinc	ppm	ASTM D5185m	0	21	34	23
Sulfur	ppm	ASTM D5185m	200	0	832	0
Visc @ 40°C	cSt	ASTM D445	46.0	48.2	50.9	48.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0212402 **Received** : 24 Apr 2024
Lab Number : 06159349 **Tested** : 25 Apr 2024
Unique Number : 10994772 **Diagnosed** : 25 Apr 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

FUQUAY - MARTIN MARIETTA
 7400 BUCKHORN DUNCAN RD
 HOLLY SPRINGS, NC
 US 27549
 Contact: DARIN HESS
 darin.hess@martinmarietta.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: