WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

[337558]

VOLVO A25G 752581
Component
Rear Axle

GEAR OIL SAE 80W140 (GA	AL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W140. Please confirm.	Sample Number		Client Info		VCP437855		
	Sample Date		Client Info		22 Apr 2024		
	Machine Age	hrs	Client Info		1662		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>900	131		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	2		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>30	0		
	Lead	ppm	ASTM D5185m	>50	0		
	Copper	ppm	ASTM D5185m	>150	13		
	Tin	ppm	ASTM D5185m	>20	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	2		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	0		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	214		
	Barium	ppm	ASTM D5185m	200	0		
	Molybdenum	ppm	ASTM D5185m	12	<1		
	Manganese	ppm	ASTM D5185m		4		
	Magnesium	ppm	ASTM D5185m	12	0		
	Calcium	ppm	ASTM D5185m	150	216		
	Phosphorus	ppm	ASTM D5185m		1190		
	Zinc	ppm	ASTM D5185m	125	90		

Sulfur

Visc @ 40°C

30131

242

ASTM D5185m 22500

ASTM D445 263

ppm





Certificate L2367

Laboratory Sample No.

: VCP437855 Lab Number : 06159454 Unique Number : 10994877 Test Package : MOB 1

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 24 Apr 2024 **Tested** : 25 Apr 2024

: 25 Apr 2024 - Wes Davis Diagnosed

ALTA EQUIPMENT/FLAGLER CONSTRUCTION EQUIPMENT LLC 8418 PALM RIVER ROAD

TAMPA, FL US 33619

Contact: KENNY HANEY khaney@flaglerce.com

T: (813)630-0077 F: (813)630-2233

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)