

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL



[518887 RENTALS] Machine Id VOLVO A25G 752643

Front Axle

GEAR OIL SAE 80W140 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W140. Please confirm.

WEAR

All component wear rates are normal.

CONTAMINATION


There is no indication of any contamination in the oil.


FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP438382	VCP426560	
Sample Date		Client Info		27 Mar 2024	28 Nov 2023	
Machine Age	hrs	Client Info		1981	1545	
Oil Age	hrs	Client Info		0	0	
Filter Age	hrs	Client Info		0	0	
Oil Changed		Client Info		Changed	N/A	
Filter Changed		Client Info		N/A	N/A	
Sample Status				NORMAL	NORMAL	
Iron	ppm	ASTM D5185m	>900	54	161	
Chromium	ppm	ASTM D5185m	>20	<1	4	
Nickel	ppm	ASTM D5185m	>10	0	2	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>30	0	2	
Lead	ppm	ASTM D5185m	>50	0	0	
Copper	ppm	ASTM D5185m	>150	8	20	
Tin	ppm	ASTM D5185m	>20	0	<1	
Vanadium	ppm	ASTM D5185m		0	0	
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Silicon	ppm	ASTM D5185m	>50	3	5	
Potassium	ppm	ASTM D5185m	>20	0	3	
Water		WC Method	>0.2	NEG	NEG	
Silt	scalar	*Visual	NONE	NONE	MODER	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Sodium	ppm	ASTM D5185m		0	0	
Boron	ppm	ASTM D5185m	400	170	232	
Barium	ppm	ASTM D5185m	200	0	3	
Molybdenum	ppm	ASTM D5185m	12	10	5	
Manganese	ppm	ASTM D5185m		2	5	
Magnesium	ppm	ASTM D5185m	12	46	2	
Calcium	ppm	ASTM D5185m	150	188	225	
Phosphorus	ppm	ASTM D5185m	1650	1166	1997	
Zinc	ppm	ASTM D5185m	125	110	94	
Sulfur	ppm	ASTM D5185m	22500	28613	34064	
Visc @ 40°C	cSt	ASTM D3103m	263	20010	128	
	001		200		120	

Contact/Location: TODD LARK - VOLVO0090





ALTA EQUIPMENT COMPANY Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. Received 5151 DR MARTIN LUTHER KING BLVD : VCP438382 : 24 Apr 2024 Lab Number : 06159467 Tested : 25 Apr 2024 FORT MYERS, FL Diagnosed Unique Number : 10994890 : 25 Apr 2024 - Wes Davis US 33905 Test Package : MOB 1 Contact: TODD LARK Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. tlark@altaequipfl.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (239)481-3302

Contact/Location: TODD LARK - VOLVO0090 Page 2 of 2

Т: