



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Area  
**ROBIN B INGRAM**  
Machine Id  
[ROBIN B INGRAM] 004 617985-4  
Component  
Port Reduction Gear  
Fluid  
CHEVRON MEROPA 320 (--- GAL)

**RECOMMENDATION**

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>MW06159844</b>	MW06159841	MW0053727
Sample Date		Client Info		<b>01 Apr 2024</b>	29 Feb 2024	01 Feb 2024
Machine Age	hrs	Client Info		<b>64747</b>	63946	63399
Oil Age	hrs	Client Info		<b>0</b>	0	63399
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>N/A</b>	N/A	Not Changd
Filter Changed		Client Info		<b>N/A</b>	Not Changd	None
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	<b>70</b>	68	29
Chromium	ppm	ASTM D5185m	>10	<b>1</b>	1	0
Nickel	ppm	ASTM D5185m	>10	<b>2</b>	2	0
Titanium	ppm	ASTM D5185m		<b>2</b>	2	0
Silver	ppm	ASTM D5185m		<b>&lt;1</b>	<1	0
Aluminum	ppm	ASTM D5185m	>25	<b>6</b>	6	3
Lead	ppm	ASTM D5185m	>100	<b>2</b>	2	0
Copper	ppm	ASTM D5185m	>50	<b>6</b>	6	3
Tin	ppm	ASTM D5185m	>10	<b>1</b>	2	0
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	<b>6</b>	6	1
Potassium	ppm	ASTM D5185m	>20	<b>3</b>	3	1
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>4</b>	4	4
Boron	ppm	ASTM D5185m	20	<b>2</b>	6	<1
Barium	ppm	ASTM D5185m		<b>16</b>	16	13
Molybdenum	ppm	ASTM D5185m	0	<b>9</b>	10	3
Manganese	ppm	ASTM D5185m		<b>2</b>	2	0
Magnesium	ppm	ASTM D5185m		<b>3</b>	13	<1
Calcium	ppm	ASTM D5185m	25	<b>103</b>	133	72
Phosphorus	ppm	ASTM D5185m	235	<b>250</b>	255	208
Zinc	ppm	ASTM D5185m		<b>4</b>	19	0
Sulfur	ppm	ASTM D5185m		<b>7423</b>	7152	7710
Acid Number (AN)	mg KOH/g	ASTM D8045	0.56	<b>0.79</b>	0.75	0.74
Visc @ 40°C	cSt	ASTM D445	304	<b>344</b>	343	342



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513

**Sample No.** : MW06159844

**Lab Number** : 06159844

**Unique Number** : 10995267

**Test Package** : MAR 2

**Received** : 24 Apr 2024

**Tested** : 25 Apr 2024

**Diagnosed** : 25 Apr 2024 - Wes Davis

**INGRAM BARGE**

900 S 3RD ST

PADUCAH, KY

US 42003

Contact: DALE MORIE

dale.morie@ingrambarga.com

T: (270)415-4467

F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)