



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
CATERPILLAR 322CL 3009 (S/N BKJ00620)
Component
Swing Drive
Fluid
{not provided} (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		CL0005363	CL0004917	CL0004102
Sample Date		Client Info		19 Apr 2024	17 Nov 2023	08 Mar 2023
Machine Age	hrs	Client Info		14290	13795	13350
Oil Age	hrs	Client Info		3200	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>400	216	207	<1
Chromium	ppm	ASTM D5185m	>10	4	4	0
Nickel	ppm	ASTM D5185m	>10	1	<1	<1
Titanium	ppm	ASTM D5185m		1	<1	0
Silver	ppm	ASTM D5185m		<1	0	0
Aluminum	ppm	ASTM D5185m	>25	5	3	0
Lead	ppm	ASTM D5185m	>50	2	<1	0
Copper	ppm	ASTM D5185m	>200	74	68	0
Tin	ppm	ASTM D5185m	>10	1	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION





There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	22	16	<1
Potassium	ppm	ASTM D5185m	>20	5	4	2
Water		WC Method	>0.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		0	0	0
Boron	ppm	ASTM D5185m		6	5	0
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		2	2	0
Manganese	ppm	ASTM D5185m		4	3	0
Magnesium	ppm	ASTM D5185m		17	16	1
Calcium	ppm	ASTM D5185m		3230	3096	3
Phosphorus	ppm	ASTM D5185m		1012	814	6
Zinc	ppm	ASTM D5185m		1192	1157	1
Sulfur	ppm	ASTM D5185m		6210	6383	85
Visc @ 40°C	cSt	ASTM D445		94.3	94.2	93.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : CL0005363
Lab Number : 06159899
Unique Number : 10995322
Test Package : CONST

Received : 24 Apr 2024
Tested : 25 Apr 2024
Diagnosed : 25 Apr 2024 - Wes Davis

PURCELL CONSTRUCTION
 3100 HIGH RIDGE RD
 CHARLOTTE, NC
 US 28270
 Contact: BEN MILKE
 ben@purcellconst.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: