



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
WIRTGEN WR250i 11WR0195
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0211552	JR0179523	JR0200163
Sample Date		Client Info		23 Apr 2024	19 Mar 2024	23 Jan 2024
Machine Age	hrs	Client Info		971	844	519
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185m	>100	21	52	56
Chromium	ppm	ASTM D5185m	>20	<1	2	2
Nickel	ppm	ASTM D5185m	>4	0	3	4
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	<1	<1
Aluminum	ppm	ASTM D5185m	>20	5	5	5
Lead	ppm	ASTM D5185m	>40	1	7	7
Copper	ppm	ASTM D5185m	>330	1	11	25
Tin	ppm	ASTM D5185m	>15	1	2	3
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	11	16	21
Potassium	ppm	ASTM D5185m	>20	5	11	15
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.3	0.3
Nitration	Abs/cm	*ASTM D7624	>20	9.9	11.0	11.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.8	25.1	24.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	1	0	3
Boron	ppm	ASTM D5185m	250	160	79	29
Barium	ppm	ASTM D5185m	10	<1	1	<1
Molybdenum	ppm	ASTM D5185m	100	213	193	40
Manganese	ppm	ASTM D5185m		<1	2	2
Magnesium	ppm	ASTM D5185m	450	670	615	233
Calcium	ppm	ASTM D5185m	3000	1690	1700	2088
Phosphorus	ppm	ASTM D5185m	1150	1007	966	1039
Zinc	ppm	ASTM D5185m	1350	1151	1080	1224
Sulfur	ppm	ASTM D5185m	4250	3662	3160	3248
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.0	21.5	21.8
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	7.9	6.5	4.9
Visc @ 100°C	cSt	ASTM D445	14.4	13.1	12.7	12.9



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0211552 **Received** : 25 Apr 2024
Lab Number : 06160120 **Tested** : 26 Apr 2024
Unique Number : 10995543 **Diagnosed** : 26 Apr 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - ASHLAND
 11047 LEADBETTER RD
 ASHLAND, VA
 US 23005

Contact: DAVID ZIEG
 dzieg@jamesriverequipment.com

T: (804)798-6001
 F: (804)798-0292