



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
3820016
 Component
Diesel Engine
 Fluid
CONOCO PHILLIPS GUARDOL ECT 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0934357	---	---
Sample Date		Client Info		21 Mar 2024	---	---
Machine Age	hrs	Client Info		3402	---	---
Oil Age	hrs	Client Info		312	---	---
Filter Age	hrs	Client Info		312	---	---
Oil Changed		Client Info		Changed	---	---
Filter Changed		Client Info		Changed	---	---
Sample Status				NORMAL	---	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	34	---	---
Chromium	ppm	ASTM D5185m	>20	<1	---	---
Nickel	ppm	ASTM D5185m	>4	0	---	---
Titanium	ppm	ASTM D5185m		1	---	---
Silver	ppm	ASTM D5185m	>3	0	---	---
Aluminum	ppm	ASTM D5185m	>20	2	---	---
Lead	ppm	ASTM D5185m	>40	4	---	---
Copper	ppm	ASTM D5185m	>330	<1	---	---
Tin	ppm	ASTM D5185m	>15	1	---	---
Vanadium	ppm	ASTM D5185m		0	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	8	---	---
Potassium	ppm	ASTM D5185m	>20	1	---	---
Fuel		WC Method	>5	<1.0	---	---
Water		WC Method	>0.2	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	*ASTM D7844	>3	0.3	---	---
Nitration	Abs/cm	*ASTM D7624	>20	10.2	---	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.7	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	---	---
Boron	ppm	ASTM D5185m	85	30	---	---
Barium	ppm	ASTM D5185m		0	---	---
Molybdenum	ppm	ASTM D5185m		8	---	---
Manganese	ppm	ASTM D5185m		<1	---	---
Magnesium	ppm	ASTM D5185m	350	794	---	---
Calcium	ppm	ASTM D5185m	1800	1451	---	---
Phosphorus	ppm	ASTM D5185m	1000	793	---	---
Zinc	ppm	ASTM D5185m	1100	906	---	---
Sulfur	ppm	ASTM D5185m	3500	3271	---	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.5	---	---
Base Number (BN)	mg KOH/g	ASTM D2896	9.5	5.2	---	---
Visc @ 100°C	cSt	ASTM D445	15.3	13.6	---	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0934357 **Received** : 25 Apr 2024
Lab Number : 06160142 **Tested** : 26 Apr 2024
Unique Number : 10995565 **Diagnosed** : 26 Apr 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

KELLER NA - LAS VEGAS
 6115 BOULDER HWY
 LAS VEGAS, NV
 US 89122
 Contact: PAT TETREAUULT
 ptetreault@keller-na.com
 T: (702)649-4466
 F: (702)649-4366

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)