



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

Contracting

Machine Id

8002 8002

Component

Rear Differential

Fluid

MOBIL DELVAC 1 SYNTHETIC GEAR SAE 75W90 (5 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0918698	WC0770784	WC0637673
Sample Date		Client Info		22 Apr 2024	22 Dec 2022	11 Nov 2021
Machine Age	hrs	Client Info		9619	6426	3345
Oil Age	hrs	Client Info		3365	3081	817
Filter Age	hrs	Client Info		3365	0	0
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Filter Changed		Client Info		Not Changd	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>500	57	87	74
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m		0	1	<1
Aluminum	ppm	ASTM D5185m	>25	<1	2	1
Lead	ppm	ASTM D5185m	>25	0	0	0
Copper	ppm	ASTM D5185m	>100	0	1	1
Tin	ppm	ASTM D5185m	>10	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	20	35	27
Potassium	ppm	ASTM D5185m	>20	<1	<1	1
Water		WC Method	>.2	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>20000	3158	696	1134
Particles >6µm		ASTM D7647	>5000	1720	379	618
Particles >14µm		ASTM D7647	>640	293	65	105
Particles >21µm		ASTM D7647	>160	99	22	35
Particles >38µm		ASTM D7647	>40	15	3	5
Particles >71µm		ASTM D7647	>10	2	0	1
Oil Cleanliness		ISO 4406 (c)	>21/19/16	19/18/15	17/16/13	17/16/14
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		3	8	7
Boron	ppm	ASTM D5185m		118	244	277
Barium	ppm	ASTM D5185m		<1	0	<1
Molybdenum	ppm	ASTM D5185m		<1	0	<1
Manganese	ppm	ASTM D5185m		3	8	8
Magnesium	ppm	ASTM D5185m		6	0	1
Calcium	ppm	ASTM D5185m		91	6	9
Phosphorus	ppm	ASTM D5185m		919	1362	1344
Zinc	ppm	ASTM D5185m		40	9	2
Sulfur	ppm	ASTM D5185m		23484	27671	20625
Visc @ 40°C	cSt	ASTM D445	120	102	96.5	98.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0918698 **Received** : 25 Apr 2024
Lab Number : 06160229 **Tested** : 26 Apr 2024
Unique Number : 10995652 **Diagnosed** : 26 Apr 2024 - Don Baldrige
Test Package : CONST (Additional Tests: PrtCount)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

CAROLINA SUNROCK
 PO BOX 25
 BUTNER, NC
 US 27509
 Contact: Leigh Dennis
 rdennis@thesunrockgroup.com
 T: (919)575-4505
 F: (919)575-0162