

WEAR	NORMAL
CONTAMINATION	
FLUID CONDITION	NORMAL

Machine Id JOHN Component 1 Axle Fluid GEAB

## JOHN DEERE 250D 638351

GEAR OIL SAE 80W90 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.

\_\_\_\_\_

## **WEAR**

All component wear rates are normal.

## **CONTAMINATION**

There is no indication of any contamination in the oil.


## **FLUID CONDITION**


-----


The condition of the oil is acceptable for the time in service.

<b>/</b>						
Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0170706		
Sample Date		Client Info		24 Apr 2024		
Machine Age	hrs	Client Info		6727		
Oil Age	hrs	Client Info		500		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		Not Changd		
Sample Status				NORMAL		
PQ		ASTM D8184	001	57		
Iron	ppm	ASTM D5185m	>601	205		
Chromium	ppm	ASTM D5185m	>11	2		
Nickel	ppm	ASTM D5185m	>10	3		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>21	4		
Lead	ppm	ASTM D5185m	>49	1		
Copper	ppm	ASTM D5185m	>21	16		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m		<1		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>31	6		
Potassium	ppm	ASTM D5185m	>20	1		
Water	pp	WC Method	>0.1	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Sodium	ppm	ASTM D5185m	>170	3		
Boron	ppm	ASTM D5185m	400	2		
Barium	ppm	ASTM D5185m	200	4		
Molybdenum	ppm	ASTM D5185m	12	20		
Manganese	ppm	ASTM D5185m		4		
Magnesium	ppm	ASTM D5185m	12	3		
Calcium	ppm	ASTM D5185m	150	18		
Phosphorus	ppm	ASTM D5185m	1650	1384		
Zinc	ppm	ASTM D5185m	125	61		
Sulfur	ppm	ASTM D5185m	22500	24516		
Visc @ 40°C	cSt	ASTM D445	143	139		

Contact/Location: RONNIE MITCHELL - JAMRIC







Contact/Location: RONNIE MITCHELL - JAMRIC Page 2 of 2

Apr24/24