



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
INTERNATIONAL 441296
Component
Diesel Engine
Fluid
MOBIL DELVAC 1300 SUPER15W40 (44 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		IL0033822	IL0026571	IL0022815
Sample Date		Client Info		25 Apr 2024	03 May 2023	15 Jun 2022
Machine Age	hrs	Client Info		8989	283892	256011
Oil Age	hrs	Client Info		0	27881	21501
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	Changed	Changed
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	63	24	38
Chromium	ppm	ASTM D5185m	>20	3	2	2
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	9	4	6
Lead	ppm	ASTM D5185m	>40	13	3	4
Copper	ppm	ASTM D5185m	>330	3	1	2
Tin	ppm	ASTM D5185m	>15	1	<1	1
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	7	6	6
Potassium	ppm	ASTM D5185m	>20	16	7	11
Fuel		WC Method	>2.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1	0.4	0.4
Nitration	Abs/cm	*ASTM D7624	>20	12.6	11.5	11.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.6	23.3	23.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		2	2	2
Boron	ppm	ASTM D5185m	0	2	4	30
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	68	61	44
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	0	1037	934	545
Calcium	ppm	ASTM D5185m		1223	1317	1758
Phosphorus	ppm	ASTM D5185m		1065	1028	743
Zinc	ppm	ASTM D5185m		1320	1271	928
Sulfur	ppm	ASTM D5185m		3634	3568	2927
Oxidation	Abs/.1mm	*ASTM D7414	>25	22.7	20.8	24.0
Base Number (BN)	mg KOH/g	ASTM D2896	9.4	6.3	7.1	9.1
Visc @ 100°C	cSt	ASTM D445	14	13.4	12.9	13.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : IL0033822
Lab Number : 06161176
Unique Number : 10996599
Test Package : FLEET

RUSH TRUCK LEASING - CHARLOTTE IDEALEASE
 1333 AMERON DR
 CHARLOTTE, NC
 US 28206
 Contact: JERRY DIXON
 dixonj@rushenterprises.com
 T: (704)333-4507
 F: (704)333-4508

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)