

Area
G. LOPES CONSTRUCTION INC./On-Road
Machine Id
311
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PCA0122610	PCA0110110	PCA0098391
Sample Date		Client Info		23 Apr 2024	20 Dec 2023	23 Aug 2023
Machine Age	mls	Client Info		386000	386000	308000
Oil Age	mls	Client Info		232000	310000	232000
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>65	25	24	17
Chromium	ppm	ASTM D5185m	>5	3	2	2
Nickel	ppm	ASTM D5185m	>3	0	<1	1
Titanium	ppm	ASTM D5185m	>5	<1	<1	1
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>35	12	11	9
Lead	ppm	ASTM D5185m	>10	0	0	<1
Copper	ppm	ASTM D5185m	>180	10	11	13
Tin	ppm	ASTM D5185m	>8	0	<1	1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>15	4	4	4
Potassium	ppm	ASTM D5185m	>20	1	1	4
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.7	0.7	0.8
Nitration	Abs/cm	*ASTM D7624	>20	8.7	8.3	9.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.1	19.9	21.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	<1	0
Boron	ppm	ASTM D5185m	0	0	11	<1
Barium	ppm	ASTM D5185m	0	0	0	2
Molybdenum	ppm	ASTM D5185m	60	60	62	66
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	974	873	979
Calcium	ppm	ASTM D5185m	1070	1157	1059	1209
Phosphorus	ppm	ASTM D5185m	1150	1026	985	1058
Zinc	ppm	ASTM D5185m	1270	1243	1205	1344
Sulfur	ppm	ASTM D5185m	2060	3190	2603	3246
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.1	15.5	16.7
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.58	8.44	8.75
Visc @ 100°C	cSt	ASTM D445	15.4	14.0	12.8	14.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0122610 **Received** : 26 Apr 2024
Lab Number : 06161708 **Tested** : 28 Apr 2024
Unique Number : 10997131 **Diagnosed** : 28 Apr 2024 - Wes Davis
Test Package : MOB 2

G LOPES CONSTRUCTION
 565 WINTHROP ST
 TAUNTON, MA
 US 02780
 Contact: BUTCH MCGRATH
 bmcgrath@glopes.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: