



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 410E 1DW410EBKNF715204
Component
Center Differential
Fluid
JOHN DEERE HY-GARD HYD/TRANS (14 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0209005	JR0201112	JR0193641
Sample Date		Client Info		24 Apr 2024	09 Feb 2024	20 Nov 2023
Machine Age	hrs	Client Info		4792	4258	3588
Oil Age	hrs	Client Info		534	2000	1588
Filter Age	hrs	Client Info		534	500	588
Oil Changed		Client Info		Not Changed	Changed	Not Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184		21	19	14
Iron	ppm	ASTM D5185m	>500	23	38	26
Chromium	ppm	ASTM D5185m	>10	0	<1	0
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	<1	2	<1
Lead	ppm	ASTM D5185m	>25	7	14	14
Copper	ppm	ASTM D5185m	>100	16	29	25
Tin	ppm	ASTM D5185m	>10	0	1	2
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	4	4	3
Potassium	ppm	ASTM D5185m	>20	0	2	0
Water		WC Method	>.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		4	0	2
Boron	ppm	ASTM D5185m	6	0	0	0
Barium	ppm	ASTM D5185m	0	<1	14	0
Molybdenum	ppm	ASTM D5185m	0	<1	<1	0
Manganese	ppm	ASTM D5185m		1	<1	1
Magnesium	ppm	ASTM D5185m	145	91	93	92
Calcium	ppm	ASTM D5185m	3570	3296	3430	3349
Phosphorus	ppm	ASTM D5185m	1290	985	1110	1018
Zinc	ppm	ASTM D5185m	1640	1103	1199	1201
Sulfur	ppm	ASTM D5185m		3793	4261	3409
Visc @ 40°C	cSt	ASTM D445	57.0	51.8	50.4	50.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : JR0209005

Lab Number : 06161722

Unique Number : 10997145

Test Package : CONST (Additional Tests: PQ)

Received : 26 Apr 2024

Tested : 28 Apr 2024

Diagnosed : 28 Apr 2024 - Wes Davis

JRE - NEW BERN
3816 MARTIN LUTHER KING BLVD
NEW BERN, NC
US 28562

Contact: NEW BERN SHOP

nick.etherdridge@jamesriverequipment.com; canastasio@wearcheckusa.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: